



## Product Guide

2024


### Description

210-0037/XX Polyurethane two-component transparent topcoat for use on veneer or solid timbers in producing furniture, kitchens doors (interior), bench tops and commercial interiors. This high build, extremely versatile topcoat is suitable for horizontal and vertical application and yields a durable, protective and silky smooth finish.

Link Products:		<b>Curing Time:</b>  Coats:1-3  Drying Times: 20 Degrees  Dry for Stacking: 5-6 Hours  Pot life :10 Hours  Colour: Clear
812-88	Polyurethane Non-Yellowing Hardener	
922-03	Polyurethane Thinner	
Mixing Ratio:		
2:1	Thin 0-5%	

### Points to note:

To obtain a uniform gloss level, it is extremely important to stir PART A well before each application. During summer or in tropical areas use slow drying thinner.

 Mixing Ratio for 2 Components 2:1 with 812-88 0 to 5% 922-03/05	 Gravity-fed Spraygun Set up/air Pressure 1.4mm 2 Bar	 Airless Set up/air Pressure 90-120psi	 Number of Spraycoats Apply 1to 3 coats	 Flash Off Flash for 10mins @20° C after each coat	 Drying Time 5-6hrs Before Sanding @20° C	During the summer, or in hot or humid temperatures, it is preferable to use a slow thinner.
SQM 7.4M2/L RFU						