RestoFinish (C/- Paint Smart Group NZ)

Chemwatch: 5544-14

Version No: 2.2 Safety Data Sheet according to the Health and Safety at Work (Hazardous Substances) Regulations 2017 Issue Date: **10/06/2022** Print Date: **15/08/2024** L.GHS.NZL.EN.E

SECTION 1 Identification of the substance / mixture and of the company / undertaking

Product Identifier	
Product name	RESTOFINISH RusGo
Chemical Name	Not Applicable
Synonyms	011-0644/011-0645/011-0655/011-0656
Proper shipping name	PHOSPHORIC ACID, SOLUTION
Chemical formula	Not Applicable
Other means of identification	Not Available
Relevant identified uses of the substance or mixture and uses advised against	
Relevant identified uses	Metal, Rust and Scale Remover
Details of the manufacturer or supplier of the safety data sheet	
Registered company name	RestoFinish (C/- Paint Smart Group NZ)
Address	10 Barberry Street Judea, Tauranga 3110 New Zealand
Telephone	07 571 8921 +61 2 4321 0339
Fax	Not Available
Website	www.restofinish.com.au/ www.paintsmart.co.nz
Email	admin@paintsmart.co.nz
Emergency telephone number	
Association / Organisation	RestoFinish (C/- Paint Smart Group NZ)
Emergency telephone numbers	0800 764766
Other emergency telephone numbers	111 (24/7)

SECTION 2 Hazards identification

Classification of the substance or mixture

Classification ^[1]	Acute Toxicity (Oral) Category 4, Skin Corrosion/Irritation Category 1A, Serious Eye Damage/Eye Irritation Category 1	
Legend:	1. Classified by Chemwatch; 2. Classification drawn from CCID EPA NZ; 3. Classification drawn from Regulation (EU) No 1272/2008 - Annex VI	
Determined by Chemwatch using GHS/HSNO criteria	6.1D (oral), 8.2A, 8.3A	

Label elements

Hazard pictogram(s)	
Signal word	Danger
Hazard statement(s)	

H302	Harmful if swallowed.
H314	Causes severe skin burns and eye damage.

Precautionary statement(s) Prevention

P260	Do not breathe mist/vapours/spray.
P264	Wash all exposed external body areas thoroughly after handling.
P280	Wear protective gloves, protective clothing, eye protection and face protection.
P270	Do not eat, drink or smoke when using this product.

Precautionary statement(s) Response

D204 . D2		
	D201	

330+P331 IF SWALLOWED: Rinse mouth. Do NOT induce vomiting. If more than 15 mins from Doctor, INDUCE VOMITING (if conscious).

D202 - D264 - D252	IF ON SIZIN (as bein) Take off immediately all contaminated electrics. Disce also with under fee showed
i dort dort dort dort dort dort dor name. Take on infinediately an oblicationated blothing. Nitse skill with water [0] shower].	
P305+P351+P338 IF IN EYES: Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing.	
P310	Immediately call a POISON CENTER/doctor/physician/first aider.
P363	Wash contaminated clothing before reuse.
P301+P312	IF SWALLOWED: Call a POISON CENTER/doctor/physician/first aider if you feel unwell.
P304+P340	IF INHALED: Remove person to fresh air and keep comfortable for breathing.
Precautionary statement(s) Storage	
P405	Store locked up.

Precautionary statement(s) Disposal

P501

Dispose of contents/container to authorised hazardous or special waste collection point in accordance with any local regulation.

SECTION 3 Composition / information on ingredients

Substances

See section below for composition of Mixtures

Mixtures

CAS No	%[weight]	Name
7664-38-2	10-30	phosphoric acid
34590-94-8	10-30	dipropylene glycol monomethyl ether
7732-18-5	30-60 <u>water</u>	
Legend:	1. Classified by Chemwatch; 2. Classification drawn from CCID EPA NZ; 3. Classification drawn from Regulation (EU) No 1272/2008 - Annex VI: 4. Classification drawn from C&L: * FU LOFL Vs available	

SECTION 4 First aid measures

Description of first aid measures		
Eye Contact	 If this product comes in contact with the eyes: Immediately hold eyelids apart and flush the eye continuously with running water. Ensure complete irrigation of the eye by keeping eyelids apart and away from eye and moving the eyelids by occasionally lifting the upper and lower lids. Continue flushing until advised to stop by the Poisons Information Centre or a doctor, or for at least 15 minutes. Transport to hospital or doctor without delay. Removal of contact lenses after an eye injury should only be undertaken by skilled personnel. 	
Skin Contact	 If skin or hair contact occurs: Immediately flush body and clothes with large amounts of water, using safety shower if available. Quickly remove all contaminated clothing, including footwear. Wash skin and hair with running water. Continue flushing with water until advised to stop by the Poisons Information Centre. Transport to hospital, or doctor. 	
Inhalation	 If fumes or combustion products are inhaled remove from contaminated area. Lay patient down. Keep warm and rested. Prostheses such as false teeth, which may block airway, should be removed, where possible, prior to initiating first aid procedures. Apply artificial respiration if not breathing, preferably with a demand valve resuscitator, bag-valve mask device, or pocket mask as trained. Perform CPR if necessary. Transport to hospital, or doctor, without delay. Inhalation of vapours or aerosols (mists, fumes) may cause lung oedema. Corrosive substances may cause lung damage (e.g. lung oedema, fluid in the lungs). As this reaction may be delayed up to 24 hours after exposure, affected individuals need complete rest (preferably in semi-recumbent posture) and must be kept under medical observation even if no symptoms are (yet) manifested. Before any such manifestation, the administration of a spray containing a dexamethasone derivative or beclomethasone derivative may be considered. This must definitely be left to a doctor or person authorised by him/her. (ICSC13719) 	
Ingestion	 For advice, contact a Poisons Information Centre or a doctor at once. Urgent hospital treatment is likely to be needed. If swallowed do NOT induce vomiting. If vomiting occurs, lean patient forward or place on left side (head-down position, if possible) to maintain open airway and prevent aspiration. Observe the patient carefully. Never give liquid to a person showing signs of being sleepy or with reduced awareness; i.e. becoming unconscious. Give water to rinse out mouth, then provide liquid slowly and as much as casualty can comfortably drink. Transport to hospital or doctor without delay. 	

Indication of any immediate medical attention and special treatment needed

For acute or short term repeated exposures to strong acids:

- Airway problems may arise from laryngeal edema and inhalation exposure. Treat with 100% oxygen initially.
- Respiratory distress may require cricothyroidotomy if endotracheal intubation is contraindicated by excessive swelling
- Intravenous lines should be established immediately in all cases where there is evidence of circulatory compromise.
- Strong acids produce a coagulation necrosis characterised by formation of a coagulum (eschar) as a result of the dessicating action of the acid on proteins in specific tissues.

INGESTION:

- Immediate dilution (milk or water) within 30 minutes post ingestion is recommended.
- DO NOT attempt to neutralise the acid since exothermic reaction may extend the corrosive injury.
- Be careful to avoid further vomit since re-exposure of the mucosa to the acid is harmful. Limit fluids to one or two glasses in an adult.
- Charcoal has no place in acid management.
- Some authors suggest the use of lavage within 1 hour of ingestion.

SKIN:

- Skin lesions require copious saline irrigation. Treat chemical burns as thermal burns with non-adherent gauze and wrapping.
 Deep second-degree burns may benefit from topical silver sulfadiazine.

EYE:

- Eye injuries require retraction of the eyelids to ensure thorough irrigation of the conjuctival cul-de-sacs. Irrigation should last at least 20-30 minutes. DO NOT use neutralising agents or any other additives. Several litres of saline are required.
- Cycloplegic drops, (1% cyclopentolate for short-term use or 5% homatropine for longer term use) antibiotic drops, vasoconstrictive agents or artificial tears may be indicated dependent on the severity of the injury.
- Steroid eye drops should only be administered with the approval of a consulting ophthalmologist).

[Ellenhorn and Barceloux: Medical Toxicology]

SECTION 5 Firefighting measures

Extinguishing media

- Water spray or fog.
- Foam.
- Dry chemical powder. BCF (where regulations permit).
- Carbon dioxide.

1

Special hazards arising from the substrate or mixture

Fire Incompatibility	Avoid contamination / mixing with oxidising agents as ignition may result
Advice for firefighters	
Fire Fighting	 Alert Fire Brigade and tell them location and nature of hazard. Wear full body protective clothing with breathing apparatus. Prevent, by any means available, spillage from entering drains or water course. Use fire fighting procedures suitable for surrounding area. Do not approach containers suspected to be hot. Cool fire exposed containers with water spray from a protected location. If safe to do so, remove containers from path of fire. Equipment should be thoroughly decontaminated after use.
Fire/Explosion Hazard	 Non combustible. Not considered to be a significant fire risk. Acids may react with metals to produce hydrogen, a highly flammable and explosive gas. Heating may cause expansion or decomposition leading to violent rupture of containers. May emit corrosive, poisonous fumes. May emit acrid smoke. carbon dioxide (CO2) phosphorus oxides (POx) other pyrolysis products typical of burning organic material. Decomposition may produce toxic fumes of:

SECTION 6 Accidental release measures

Personal precautions, protective equipment and emergency procedures

See section 8

Environmental precautions

See section 12

Methods and material for containment and cleaning up

Minor Spills	 Environmental hazard - contain spillage. Drains for storage or use areas should have retention basins for pH adjustments and dilution of spills before discharge or disposal of material. Check regularly for spills and leaks. Clean up all spills immediately. Avoid breathing vapours and contact with skin and eyes. Control personal contact with the substance, by using protective equipment. Contain and absorb spill with sand, earth, inert material or vermiculite. Wipe up. Place in a suitable, labelled container for waste disposal.
Major Spills	 Environmental hazard - contain spillage. Clear area of personnel and move upwind. Alert Fire Brigade and tell them location and nature of hazard. Wear full body protective clothing with breathing apparatus. Prevent, by any means available, spillage from entering drains or water course. Consider evacuation (or protect in place). Stop leak if safe to do so. Contain spill with sand, earth or vermiculite. Collect recoverable product into labelled containers for recycling. Neutralise/decontaminate residue (see Section 13 for specific agent). Collect solid residues and seal in labelled drums for disposal. Wash area and prevent runoff into drains. After clean up operations, decontaminate and launder all protective clothing and equipment before storing and re-using. If contamination of drains or waterways occurs, advise emergency services.

Personal Protective Equipment advice is contained in Section 8 of the SDS.

SECTION 7 Handling and storage

Precautions for safe handling	
Safe handling	DO NOT allow clothing wet with material to stay in contact with skin
	The tendency of many ethers to form explosive peroxides is well documented. Ethers lacking non-methyl hydrogen atoms adjacent to the
	ether link are thought to be relatively safe

	• DO NOT concentrate by evaporation, or evaporate extracts to dryness, as residues may contain explosive peroxides with DETONATION
	potential.
	 Before any distillation process remove trace periodes by shaking with excess 5% aqueous ferrous sulfate solution or by percolation
	through a column of activated alumina.
	Distillation results in uninhibited ether distillate with considerably increased hazard because of risk of peroxide formation on storage.
	 Add inhibitor to any distillate as required. When selvents have been feed from percentide by percention through columns of activated elymins, the shocked percentide must
	 When solvents have been need from perioxides by periodiation introgen columns of activated alumnina, the associated perioxides must promitly be described by treatment with polar solvents such as methanol or water, which should then be disposed of safety.
	The substance accumulates peroxides which may become hazardous only if it evaporates or is distilled or otherwise treated to concentrate
	the peroxides. The substance may concentrate around the container opening for example.
	Purchases of peroxidisable chemicals should be restricted to ensure that the chemical is used completely before it can become peroxidised.
	• A responsible person should maintain an inventory of peroxidisable chemicals or annotate the general chemical inventory to indicate
	which chemicals are subject to peroxidation. An expiration date should be determined. The chemical should either be treated to remove
	 The person or plaboratory receiving the chemical should record a receipt date on the bottle. The individual opening the container should
	add an opening date.
	Unopened containers received from the supplier should be safe to store for 18 months.
	 Opened containers should not be stored for more than 12 months.
	 Avoid all personal contact, including inhalation. Work protective debting debting of expression account
	Veal protective country when this of exposure occurs. I lise in a well-ventilated area
	WARNING: To avoid violent reaction, ALWAYS add material to water and NEVER water to material.
	Avoid smoking, naked lights or ignition sources.
	Avoid contact with incompatible materials.
	When handling, DO NOT eat, drink or smoke.
	Keep containers securely sealed when not in use.
	A Void physical damlage to containers. Always wash bands with soan and water after bandling
	 Work clothes should be laundered separately. Launder contaminated clothing before re-use.
	Use good occupational work practice.
	Observe manufacturer's storage and handling recommendations contained within this SDS.
	Atmosphere should be regularly checked against established exposure standards to ensure safe working conditions are maintained.
	Store in original containers.
	Keep containers securely sealed.
Other information	 Store in a cool, dry, well-ventilated area. Store oursy from incompatible metricile and foodstuff containers.
	Store away non-incompatible materials and rootstan containers. Protect containers against physical damage and check regularly for leaks.
	 Observe manufacturer's storage and handling recommendations contained within this SDS.
Conditions for safe storage, in	ncluding any incompatibilities
	DO NOT use aluminium or galvanised containers
	DO NOT use aluminium or galvanised containers Check regularly for spills and leaks
	 DO NOT use aluminium or galvanised containers Check regularly for spills and leaks Lined metal can, lined metal pail/ can.
	 DO NOT use aluminium or galvanised containers Check regularly for spills and leaks Lined metal can, lined metal pail/ can. Plastic pail.
	 DO NOT use aluminium or galvanised containers Check regularly for spills and leaks Lined metal can, lined metal pail/ can. Plastic pail. Polyliner drum.
	 DO NOT use aluminium or galvanised containers Check regularly for spills and leaks Lined metal can, lined metal pail/ can. Plastic pail. Polyliner drum. Packing as recommended by manufacturer. Check all containers are clearly labelled and free from leaks.
	 DO NOT use aluminium or galvanised containers Check regularly for spills and leaks Lined metal can, lined metal pail/ can. Plastic pail. Polyliner drum. Packing as recommended by manufacturer. Check all containers are clearly labelled and free from leaks. For low viscosity materials
	 DO NOT use aluminium or galvanised containers Check regularly for spills and leaks Lined metal can, lined metal pail/ can. Plastic pail. Polyliner drum. Packing as recommended by manufacturer. Check all containers are clearly labelled and free from leaks. For low viscosity materials Drums and jerricans must be of the non-removable head type.
Suitable container	 DO NOT use aluminium or galvanised containers Check regularly for spills and leaks Lined metal can, lined metal pail/ can. Plastic pail. Polyliner drum. Packing as recommended by manufacturer. Check all containers are clearly labelled and free from leaks. For low viscosity materials Drums and jerricans must be of the non-removable head type. Where a can is to be used as an inner package, the can must have a screwed enclosure.
Suitable container	 DO NOT use aluminium or galvanised containers Check regularly for spills and leaks Lined metal can, lined metal pail/ can. Plastic pail. Polyliner drum. Packing as recommended by manufacturer. Check all containers are clearly labelled and free from leaks. For low viscosity materials Drums and jerricans must be of the non-removable head type. Where a can is to be used as an inner package, the can must have a screwed enclosure. For materials with a viscosity of at least 2680 cSt. (23 deg. C) and solids (between 15 C deg. and 40 deg C.):
Suitable container	 DO NOT use aluminium or galvanised containers Check regularly for spills and leaks Lined metal can, lined metal pail/ can. Plastic pail. Polyliner drum. Packing as recommended by manufacturer. Check all containers are clearly labelled and free from leaks. For low viscosity materials Drums and jerricans must be of the non-removable head type. Where a can is to be used as an inner package, the can must have a screwed enclosure. For materials with a viscosity of at least 2680 cSt. (23 deg. C) and solids (between 15 C deg. and 40 deg C.): Removable head packaging; Canse with friction closures and
Suitable container	 DO NOT use aluminium or galvanised containers Check regularly for spills and leaks Lined metal can, lined metal pail/ can. Plastic pail. Polyliner drum. Packing as recommended by manufacturer. Check all containers are clearly labelled and free from leaks. For low viscosity materials Drums and jerricans must be of the non-removable head type. Where a can is to be used as an inner package, the can must have a screwed enclosure. For materials with a viscosity of at least 2680 cSt. (23 deg. C) and solids (between 15 C deg. and 40 deg C.): Removable head packaging; Cans with friction closures and Iow pressure tubes and cartridges
Suitable container	 DO NOT use aluminium or galvanised containers Check regularly for spills and leaks Lined metal can, lined metal pail/ can. Plastic pail. Polyliner drum. Packing as recommended by manufacturer. Check all containers are clearly labelled and free from leaks. For low viscosity materials Drums and jerricans must be of the non-removable head type. Where a can is to be used as an inner package, the can must have a screwed enclosure. For materials with a viscosity of at least 2680 cSt. (23 deg. C) and solids (between 15 C deg. and 40 deg C.): Removable head packaging; Cans with friction closures and Iow pressure tubes and cartridges may be used.
Suitable container	 DO NOT use aluminium or galvanised containers Check regularly for spills and leaks Lined metal can, lined metal pail/ can. Plastic pail. Polyliner drum. Packing as recommended by manufacturer. Check all containers are clearly labelled and free from leaks. For low viscosity materials Drums and jerricans must be of the non-removable head type. Where a can is to be used as an inner package, the can must have a screwed enclosure. For materials with a viscosity of at least 2680 cSt. (23 deg. C) and solids (between 15 C deg. and 40 deg C.): Removable head packaging; Cans with friction closures and Iow pressure tubes and cartridges may be used.
Suitable container	 DO NOT use aluminium or galvanised containers Check regularly for spills and leaks Lined metal can, lined metal pail/ can. Plastic pail. Polyliner drum. Packing as recommended by manufacturer. Check all containers are clearly labelled and free from leaks. For low viscosity materials Drums and jerricans must be of the non-removable head type. Where a can is to be used as an inner package, the can must have a screwed enclosure. For materials with a viscosity of at least 2680 cSt. (23 deg. C) and solids (between 15 C deg. and 40 deg C.): Removable head packaging; Cans with friction closures and Iow pressure tubes and cartridges may be used. Where combination packages are used, and the inner packages are of glass, porcelain or stoneware, there must be sufficient inert
Suitable container	 DO NOT use aluminium or galvanised containers Check regularly for spills and leaks Lined metal can, lined metal pail/ can. Plastic pail. Polyliner drum. Packing as recommended by manufacturer. Check all containers are clearly labelled and free from leaks. For low viscosity materials Drums and jerricans must be of the non-removable head type. Where a can is to be used as an inner package, the can must have a screwed enclosure. For materials with a viscosity of at least 2680 cSt. (23 deg. C) and solids (between 15 C deg. and 40 deg C.): Removable head packaging; Cans with friction closures and Iow pressure tubes and cartridges may be used. Where combination packages are used, and the inner packages are of glass, porcelain or stoneware, there must be sufficient inert cushioning material in contact with inner and outer packages unless the outer packaging is a close fitting moulded plastic box and the substances are not incompatible with the plastic.
Suitable container	 DO NOT use aluminium or galvanised containers Check regularly for spills and leaks Lined metal can, lined metal pail/ can. Plastic pail. Polyliner drum. Packing as recommended by manufacturer. Check all containers are clearly labelled and free from leaks. For low viscosity materials Drums and jerricans must be of the non-removable head type. Where a can is to be used as an inner package, the can must have a screwed enclosure. For materials with a viscosity of at least 2680 cSt. (23 deg. C) and solids (between 15 C deg. and 40 deg C.): Removable head packaging; Cans with friction closures and low pressure tubes and cartridges may be used. Where combination packages are used, and the inner packages are of glass, porcelain or stoneware, there must be sufficient inert cushioning material in contact with inner and outer packages unless the outer packaging is a close fitting moulded plastic box and the substances are not incompatible with the plastic.
Suitable container	 DO NOT use aluminium or galvanised containers Check regularly for spills and leaks Lined metal can, lined metal pail/ can. Plastic pail. Polyliner drum. Packing as recommended by manufacturer. Check all containers are clearly labelled and free from leaks. For low viscosity materials Drums and jerricans must be of the non-removable head type. Where a can is to be used as an inner package, the can must have a screwed enclosure. For materials with a viscosity of at least 2680 cSt. (23 deg. C) and solids (between 15 C deg. and 40 deg C.): Removable head packaging; Cans with friction closures and low pressure tubes and cartridges may be used. Where combination packages are used, and the inner packages are of glass, porcelain or stoneware, there must be sufficient inert cushioning material in contact with inner and outer packages unless the outer packaging is a close fitting moulded plastic box and the substances are not incompatible with the plastic.
Suitable container	 DO NOT use aluminium or galvanised containers Check regularly for spills and leaks Lined metal can, lined metal pail/ can. Plastic pail. Polyliner drum. Packing as recommended by manufacturer. Check all containers are clearly labelled and free from leaks. For low viscosity materials Drums and jerricans must be of the non-removable head type. Where a can is to be used as an inner package, the can must have a screwed enclosure. For materials with a viscosity of at least 2680 cSt. (23 deg. C) and solids (between 15 C deg. and 40 deg C.): Removable head packaging; Cans with friction closures and low pressure tubes and cartridges may be used. Where combination packages are used, and the inner packages are of glass, porcelain or stoneware, there must be sufficient inert cushioning material in contact with inner and outer packages unless the outer packaging is a close fitting moulded plastic box and the substances are not incompatible with the plastic. Phosphoric acid: is a medium-strong acid which produces violent reaction with bases may produce violent react when water is added to the concentrated form
Suitable container	 DO NOT use aluminium or galvanised containers Check regularly for spills and leaks Lined metal can, lined metal pail/ can. Plastic pail. Polyliner drum. Packing as recommended by manufacturer. Check all containers are clearly labelled and free from leaks. For low viscosity materials Drums and jerricans must be of the non-removable head type. Where a can is to be used as an inner package, the can must have a screwed enclosure. For materials with a viscosity of at least 2680 cSt. (23 deg. C) and solids (between 15 C deg. and 40 deg C.): Removable head packaging; Cans with friction closures and low pressure tubes and cartridges may be used. Where combination packages are used, and the inner packages are of glass, porcelain or stoneware, there must be sufficient inert cushioning material in contact with inner and outer packages unless the outer packaging is a close fitting moulded plastic box and the substances are not incompatible with the plastic. Phosphoric acid: is a medium-strong acid which produces violent reaction with bases may produce violent react when water is added to the concentrated form reacts violently with solutions containing ammonia or bleach, azo compounds, epoxides and other polymerisable compounds
Suitable container	 DO NOT use aluminium or galvanised containers Check regularly for spills and leaks Lined metal can, lined metal pail/ can. Plastic pail. Polyliner drum. Packing as recommended by manufacturer. Check all containers are clearly labelled and free from leaks. For low viscosity materials Drums and jerricans must be of the non-removable head type. Where a can is to be used as an inner package, the can must have a screwed enclosure. For materials with a viscosity of at least 2680 cSt. (23 deg. C) and solids (between 15 C deg. and 40 deg C.): Removable head packaging; Cans with friction closures and low pressure tubes and cartridges may be used. Where combination packages are used, and the inner packages are of glass, porcelain or stoneware, there must be sufficient inert cushioning material in contact with inner and outer packages unless the outer packaging is a close fitting moulded plastic box and the substances are not incompatible with the plastic.
Suitable container	 DO NOT use aluminium or galvanised containers Check regularly for spills and leaks Lined metal can, lined metal pail/ can. Plastic pail. Polyliner drum. Packing as recommended by manufacturer. Check all containers are clearly labelled and free from leaks. For low viscosity materials Drums and jerricans must be of the non-removable head type. Where a can is to be used as an inner package, the can must have a screwed enclosure. For materials with a viscosity of at least 2680 cSt. (23 deg. C) and solids (between 15 C deg. and 40 deg C.): Removable head packaging; Cans with friction closures and low pressure tubes and cartridges may be used. Where combination packages are used, and the inner packages are of glass, porcelain or stoneware, there must be sufficient inert cushioning material in contact with inner and outer packages unless the outer packaging is a close fitting moulded plastic box and the substances are not incompatible with the plastic. Phosphoric acid: is a medium-strong acid which produces violent reaction with bases may produce violent react when water is added to the concentrated form reacts, possibly violently with amines, aldehydes, alkanolamines, alcohols, alkylene oxides, aminoa, ammonia hydroxide, calcium oxide, cyanides, epichlorohydrin, esters, halogenated organics, isocyanates, ketones, oleum, organic anhydrides, sodium totsprette
Suitable container	 DO NOT use aluminium or galvanised containers Check regularly for spills and leaks Lined metal can, lined metal pail/ can. Plastic pail. Polyliner drum. Packing as recommended by manufacturer. Check all containers are clearly labelled and free from leaks. For low viscosity materials Drums and jerricans must be of the non-removable head type. Where a can is to be used as an inner package, the can must have a screwed enclosure. For materials with a viscosity of at least 2680 cSt. (23 deg. C) and solids (between 15 C deg. and 40 deg C.): Removable head packaging; Cans with friction closures and low pressure tubes and cartridges may be used. Where combination packages are used, and the inner packages are of glass, porcelain or stoneware, there must be sufficient inert cushioning material in contact with inner and outer packages unless the outer packaging is a close fitting moulded plastic box and the substances are not incompatible with the plastic. Phosphoric acid: is a medium-strong acid which produces violent reaction with bases may produce violent react when water is added to the concentrated form reacts violently with solutions containing ammonia or bleach, azo compounds, epoxides and other polymerisable compounds reacts, possibly violently with amines, aldehydes, alkanolamines, alcohols, alkylene oxides, amides, ammonia hydroxide, calcium oxide, cyanides, epichlorohydrin, esters, halogenated organics, isocyanates, ketones, oleum, organic anhydrides, sodium tetraborate, sulfides, sulfuric acid, strong oxidisers, vinyl acetate
Suitable container	 DO NOT use aluminium or galvanised containers Check regularly for spills and leaks Lined metal can, lined metal pail/ can. Plastic pail. Polyliner drum. Packing as recommended by manufacturer. Check all containers are clearly labelled and free from leaks. For low viscosity materials Drums and jerricans must be of the non-removable head type. Where a can is to be used as an inner package, the can must have a screwed enclosure. For materials with a viscosity of at least 2680 cSt. (23 deg. C) and solids (between 15 C deg. and 40 deg C.): Removable head packaging; Cans with friction closures and low pressure tubes and cartridges may be used. - Where combination packages are used, and the inner packages are of glass, porcelain or stoneware, there must be sufficient inert cushioning material in contact with inner and outer packages unless the outer packaging is a close fitting moulded plastic box and the substances are not incompatible with the plastic. Phosphoric acid: is a medium-strong acid which produces violent reaction with bases may produce violent react when water is added to the concentrated form reacts violently with solutions containing ammonia or bleach, azo compounds, epoxides and other polymerisable compounds reacts, possibly violently with animes, aldehydes, alkanolamines, alcohols, alkylene oxides, animosia, anmonia, anmonia hydroxide, calcium oxide, cyanides, epichlorohydrin, esters, halogenated organics, isocyanates, ketones, oleum, organic anhydrides, sodium tetraborate, sulfides, sulfuric acid, strong oxidisers, vinyl acetate forms explosive mixtures with nitromethane at elevated temperatures attacks many metals producing hydrogen gas<!--</th-->
Suitable container	 DO NOT use aluminium or galvanised containers Check regularly for spills and leaks Lined metal can, lined metal pail/ can. Plastic pail. Polyliner drum. Packing as recommended by manufacturer. Check all containers are clearly labelled and free from leaks. For low viscosity materials Drums and jerricans must be of the non-removable head type. Where a can is to be used as an inner package, the can must have a screwed enclosure. For materials with a viscosity of at least 2680 cSt. (23 deg. C) and solids (between 15 C deg. and 40 deg C.): Removable head packaging; Cans with friction closures and low pressure tubes and cartridges may be used. Where combination packages are used, and the inner packages unless the outer packaging is a close fitting moulded plastic box and the substances are not incompatible with the plastic. Phosphoric acid: is a medium-strong acid which produces violent reaction with bases may produce violent react when water is added to the concentrated form reacts, violently with solutions containing ammonia or bleach, azo compounds, epoxides and other polymerisable compounds reacts, possibly violently with amines, alcohols, alkylene oxides, aminoia, ammonia hydroxide, calcium oxide, cyanides, epichlorohydrin, esters, halogenated organics, isocyanates, ketones, oleum, organic anhydrides, sodium tetraborate, sulfides, sulfuric acid, strong oxidisers, vinyl acetate forms explosive mixtures with nitromethane at elevated temperature does not attack stainless steel, copper or its alloys
Suitable container	 Do NOT use aluminium or galvanised containers Check regularly for spills and leaks Lined metal can, lined metal pail/ can. Plastic pail. Polyliner drum. Packing as recommended by manufacturer. Check all containers are clearly labelled and free from leaks. For low viscosity materials Drums and jerricans must be of the non-removable head type. Where a can is to be used as an inner package, the can must have a screwed enclosure. For materials with a viscosity of at least 2680 cSt. (23 deg. C) and solids (between 15 C deg. and 40 deg C.): Removable head packaging; Cans with friction closures and low pressure tubes and cartridges may be used. Where combination packages are used, and the inner packages are of glass, porcelain or stoneware, there must be sufficient inert cushioning material in contact with inner and outer packages unless the outer packaging is a close fitting moulded plastic box and the substances are not incompatible with the plastic. Phosphoric acid: is a medium-strong acid which produces violent reaction with bases may produce violent react when water is added to the concentrated form reacts, violently with solutions containing mmonia or bleach, azo compounds, epoxides and other polymerisable compounds reacts, possibly violently with amines, aldehydes, alkanolamines, alcohols, alkylene oxides, aminola, ammonia hydroxide, calcium oxide, cyanides, epichlorohydrin, esters, halogenated organics, isocyanates, ketones, oleum, organic anhydrides, sodium tetraborate, sulficient index states the attack stanles steel, copper or its alloys at elevated temperatures attack smany metals producing hydrogen gas at elevated temperature does not attack stanles steel, copper or its alloys attacks glass, ceramics, and some plastics, rubber and coatings
Suitable container	 DO NOT use aluminium or galvanised containers Check regularly for spills and leaks Lined metal can, lined metal pail/ can. Plastic pail. Polyliner drum. Pokliner drum. Pokliner drum. Check all containers are clearly labelled and free from leaks. For low viscosity materials Drums and jerricans must be of the non-removable head type. Where a can is to be used as an inner package, the can must have a screwed enclosure. For materials with a viscosity of at least 2680 cSt. (23 deg. C) and solids (between 15 C deg. and 40 deg C.): Removable head packaging; Cans with friction closures and low pressure tubes and cartridges may be used. Where combination packages are used, and the inner packages are of glass, porcelain or stoneware, there must be sufficient inert cushioning material in contact with the plastic. Phosphoric acid: is a medium-strong acid which produces violent reaction with bases may produce violent react when water is added to the concentrated form. reacts violently with solutions containing ammonia or bleach, azo compounds, epoxides and other polymerisable compounds reacts violently with mines, addehydes, alkanolamines, alcohols, alkylene oxides, amides, ammonia hydroxide, calcium oxide, cyanides, sulficies, sulfuric acid, strong oxidies, vinyl acetate form explosive mixtures with nitrom thane at elevated temperature does not attack stainless sted, copper or is alloys at room temperature does not attack stainless sted, copper or is alloys at close stainles, add some plastics, ubber and coatings Inorganic acids are generally soluble in water with the release of hydrogen ions. The resulting solutions have pH's of less than 7.0.
Suitable container	 DO NOT use aluminium or galvanised containers Check regularly for spills and leaks Lined metal can, lined metal pail/ can. Plastic pail. Polyliner drum. Packing as recommended by manufacturer. Check all containers are clearly labelled and free from leaks. For low viscosity materials Drums and jerricans must be of the non-removable head type. Where a can is to be used as an inner package, the can must have a screwed enclosure. For materials with a viscosity of at least 2680 cSt. (23 deg. C) and solids (between 15 C deg. and 40 deg C.): Removable head packaging; Cans with friction closures and low pressure tubes and cartridges may be used. - Where combination packages are used, and the inner packages are of glass, porcelain or stoneware, there must be sufficient inert cushioning material in contact with inner and outer packages unless the outer packaging is a close fitting moulded plastic box and the substances are not incompatible with the plastic. Phosphoric acid: is a medium-strong acid which produces violent reaction with bases may produce violent react when water is added to the concentrated form reacts, possibly violently with amines, aldehydes, alkanolamines, alcohols, alkylene oxides, amides, ammonia, ammonia hydroxide, calcitum oxide, cynides, geirblorchydrin, esters, halogenated organics, isocyanates, ketones, oleum, organic anhydrides, sodium tetraborate, sufficies, sufficies stainless the outer gas and other polymerisable compounds reacts, possibly violently with amines, aldehydes, alkanolamines, alcohols, alkylene oxides, amides, ammonia, ammonia hydroxide, calcitum oxide, cynides, geirblorchydrin, esters, halogenated organics, isocyanates, ketones, oleum, organic anhydrides, sodium tetraborat
Suitable container	 DO NOT use aluminium or galvanised containers Check regularly for spills and leaks Lined metal can, lined metal pail/ can. Plastic pail. Polyliner drum. Packing as recommended by manufacturer. Check all containers are clearly labelled and free from leaks. For low viscosity materials Drums and jerricans must be of the non-removable head type. Where a can is to be used as an inner package, the can must have a screwed enclosure. For materials with a viscosity of at least 2680 cSt. (23 deg. C) and solids (between 15 C deg. and 40 deg C.): Removable head packaging; Cans with friction closures and low pressure tubes and cartridges may be used. Where combination packages are used, and the inner packages are of glass, porcelain or stoneware, there must be sufficient inert cushioning material in contact with inner and outer packages unless the outer packaging is a close fitting moulded plastic box and the substances are not incompatible with the plastic. Phosphoric acid: is a medium-strong acid which produces violent reaction with bases may produce violent react when water is added to the concentrated form reacts violently with solutions containing ammonia or bleach, azo compounds, epoxides and other polymerisable compounds reacts violently with solutions containing ammonia or bleach, azo compounds, epoxides, and other polymerisable compounds reacts violently with solutions containing atmonia or bleach, azo compounds, epoxides, and other polymerisable compounds reacts violently with solutions containing atmonia or bleach, azo compounds, epoxides, and other polymerisable compounds reacts violently with solutions containing atmonia or bleach, azo compou
Suitable container	 DO NOT use aluminium or galvanised containers Check regularly for spills and leaks Lined metal can, lined metal pail/ can. Plastic pail. Polyliner drum. Packing as recommended by manufacturer. Check all containers are clearly labelled and free from leaks. For low viscosity materials Drums and jerricans must be of the non-removable head type. Where a can is to be used as an inner package, the can must have a screwed enclosure. For materials with a viscosity of at least 2680 cSt. (23 deg. C) and solids (between 15 C deg. and 40 deg C.): Removable head packaging; Cans with friction closures and low pressure tubes and cartridges may be used. Where combination packages are used, and the inner packages are of glass, porcelain or stoneware, there must be sufficient inert cushioning material in contact with inner and outer packages are of glass, porcelain or stoneware, there must be sufficient inert cushioning material in contact with inner and outer packages are of glass, porcelain or stoneware, there must be sufficient inert cushioning material in contact with inner and outer packages are of glass, porcelain or stoneware, there must be sufficient inert cushioning material in contact with inner and outer packages are of glass, porcelain or stoneware, there must be sufficient inert cushioning material in contact with inner and outer packages are of glass, porcelain or stoneware, there must be sufficient inert cushioning attemption with bases is a medium-strong acid which produces violent reaction with bases may produce violently with solutions containing ammonia or bleach, azo compounds, epoxides, animonia, ammonia hydroxide, calcium oxide, cyanides, epichlorohydrin, esters, halogenated organics, ialcoynates, ketones, oleum, organic anhydrides, solduru tetraborate, sulfides, sulfuric acid,
Suitable container	 DO NOT use aluminium or galvanised containers Check regularly for spills and leaks Lined metal can, lined metal pail/ can. Plastic pail. Polyliner drum. Packing as recommended by manufacturer. Check all containers are clearly labelled and free from leaks. For low viscosity materials Drums and jerricans must be of the non-removable head type. Where a can is to be used as an inner package, the can must have a screwed enclosure. For materials with a viscosity of at least 2680 cSt. (23 deg. C) and solids (between 15 C deg. and 40 deg C.): Removable head packaging: Cans with friction closures and low pressure tubes and cartridges may be used. Where combination packages are used, and the inner packages are of glass, porcelain or stoneware, there must be sufficient inert cushioning material in contact with inner and outer packages are of glass, porcelain or stoneware, there must be sufficient inert cushioning material in contact with inner and outer packages are of glass, porcelain or stoneware, there must be sufficient inert cushioning material in contact with inner and outer packages unless the outer packaging is a close fitting moulded plastic box and the substances are not incompatible with the plastic. Phosphoric acid: is a medium-strong acid which produces violent reaction with bases may produce violent react when water is added to the concentrated form reacts, possibly violently with amines, aldehydes, alkanolamines, alcohols, alkylene oxides, ammonia, ammonia hydroxide, calcium oxide, cyanides, epichlorohydrin, esters, halogenated organics, isocyanates, ketones, oleum, organic anhydrides, sodium tetraborate, sulfides, sulfur acid, strong oxidienry, hydrogen gas at elevated temperatures datack stanless stele
Suitable container	 bOx NoT use aluminium or galvanised containers Check regularly for spills and leaks Lined metal can, lined metal pail/ can. Plastic pail. Polyliner drum. Packing as recommended by manufacturer. Check all containers are clearly labelled and free from leaks. For low viscosity materials Drums must be of the non-removable head type. Where a can is to be used as an inner package, the can must have a screwed enclosure. For materials with a viscosity of at least 2680 cSt. (23 deg. C) and solids (between 15 C deg. and 40 deg C.): Removable head packaging; Cans with friction closures and low pressure tubes and cartridges may be used. Where combination packages are used, and the inner packages are of glass, porcelain or stoneware, there must be sufficient inert cushoning material in contact with inner and outer packages unless the outer packaging is a close fitting moulded plastic box and the substances are not incompatible with the plastic. Phosphoric acid: is a medium-strong acid which produces violent reaction with bases may porduce violent with aveir is added to the concentrated form reacts violently with solutions containing ammonia or bleach, azo compounds, epoxides and other polymerisable compounds reacts violently with solutions containing atmomia or bleach, azo compounds, epoxides and other polymerisable compounds reacts plositio withures with informethane at elevated temperatures with standed to the reating alkanolamines, alcohols, alkylene oxides, and onia, ammonia hydroxide, calcium oxide, cyanides, soluting atmosting ording hydrogen gas at room themperature does not attack stainless steel, copper or its alloys attacks glass, ceramics, and some plastics, rubber and coatings Inorganic acids are generally soluble in water with the release of hydrogen ions. The resulting so
Suitable container	 bD NOT use aluminium or galvanised containers Check regularly for spills and leaks Lined metal can, lined metal pail/ can. Plastic pail. Polytiner drum. Packing as recommended by manufacturer. Check all containers are clearly labelled and free from leaks. For low viscosity materials Drums must be of the non-removable head type. Where a can is to be used as an inner package, the can must have a screwed enclosure. For materials with a viscosity of at least 2680 cSt. (23 deg. C) and solids (between 15 C deg. and 40 deg C.): Removable head packaging; Cans with friction closures and low pressure tubes and carrindges may be used. . Where combination packages are used, and the inner packages are of glass, porcelain or stoneware, there must be sufficient inert cushioning material in contact with inner and outer packages unless the outer packaging is a close fitting moulded plastic box and the substances are not incompatible with the plastic. Prosphoric acid: Is a medium-strong acid which produces violent reaction with bases may produce violent react when water is added to the concentrated form reacts, possibly violently with amines, aldehydes, alkanolamines, alcohols, alkylene oxides, amides, ammonia, ammonia hydroxide, calcium oxide, cyanides, epichicrohydrin, esters, halogenated organics, iscoyanates, ketones, oleum, organic anhydrides, sodium tetraborate, sulfides, and y tetra and test staffices and the rance staffices and y endities, sodium tetraborate, sulfides; and may reacted temperatures attacks many metals producing hydrogen gas at room temperature does not attack stainless steel, copper or its alloys tates del senteriatios; and some plastics, rubber and coacting Inorganic acids are generally soluble in water with the release of hydrogen ions. The resulting solutions have pH's of less than
Suitable container	 bD NOT use aluminium or galvanised containers Check regularly for spills and leaks Lined metal can, lined metal pail/ can. Plastic pail. Polyliner drum. Packing as recommended by manufacturer. Check all containers are clearly labeled and free from leaks. For low viscosity materials Drums and jerricans must be of the non-removable head type. Where a can is to be used as an inner package, the can must have a screwed enclosure. For materials with a viscosity of at least 2680 cSt. (23 deg. C) and solids (between 15 C deg. and 40 deg C.): Removable head packaging; Cans with friction closures and low pressure tubes and cartridges may be used. - Where combination packages are used, and the inner packages are of glass, porcelain or stoneware, there must be sufficient inert cushoning material in contact with inner and outer packages are least 2680 cSt. (23 deg. C) and solids (between 15 C deg. and 40 deg C.): Removable head packaging; Cans with friction closures and low pressure tubes and cartridges may be used. - Where combination packages are used, and the inner packages are of glass, porcelain or stoneware, there must be sufficient inert cushoning material in contact with inner and outer packages unless the outer packaging is a close fitting moulded plastic box and the substances are not incompatible with the plastic. Prosphoric acid: is a medium-strong acid which produces violent reaction with bases may produce violent react when water is added to the concentrated form reacts violently with solutions containing ammonia or bleach, azo compounds, epoxides and other polymerisable compounds reacts usideling, sulfuric acid, strong oxidisers, vinyl acetate forms explosive mixtures with nitromethane at elevated temperatures attack many metals producing hydro
Suitable container	 bD NOT use aluminium or galvanised containers Check regularly for spills and leaks Lined metal can, lined metal pail/ can. Pasitic pail. Polyliner drum. Packing as recommended by manufacturer. Check all containers are clearly labelled and free from leaks. For low viscosity materials Drums and jerricans must be of the non-removable head type. Where a can is to be used as an inner package, the can must have a screwed enclosure. For materials with a viscosity of at least 2680 cSt. (23 deg. C) and solids (between 15 C deg. and 40 deg C.): Removable head packaging: Canse with friction closures and low pressure tubes and cartridges may be used. Where combination packages are used, and the inner packages are of glass, porcelain or stoneware, there must be sufficient inert cushoining material in contact with inner and outer packages unless the outer packaging is a close fitting moulded plastic box and the substances are not incompatible with the plastic. Phosphoric acid: is a medium-strong acid which produces violent reaction with bases may produce violent react when water is added to the concentrated form reacts, polssibly violently with amines, aldehydes, alkanolamines, alcohydis, alkylene oxides, amides, ammonia, ammonia hydroxide, calcium otide, cynidrydin, esters, halogenated organics, isocyanates, ketones, oleum, organic anhydrides, sodium tetraborate, sulfides, sulfuric acid, strong oxidisers, vinyl acetate forms explosive mixtures with nitromethane at elevated temperature does not attack stainless stele, copper or its alloys at actos fare generally soluble in water with the release of hydrogen ions. The resulting solutions have pH's of less than 7.0. Inorganic acids are generally soluble in water with the release of hydrogen ions. The resulting solutions have pH's of less than 7.0. Inorgani
Suitable container	 bOr Vot use aluminium or galvanised containers Check regularly for spills and leaks Lined metal can, lined metal pail/ can. Plastic pail. Polyliner drum. Packing as recommended by manufacturer. Check all containers are clearly labelled and free from leaks. For low viscosity materials Drums and jerricans must be of the non-removable head type. Where a can is to be used as an inner package, the can must have a screwed enclosure. For mass and jerricans must be of the non-removable head type. Where a can is to be used as an inner package, the can must have a screwed enclosure. For materials with a viscosures and Iow pressure tubes and cartridges may be used. Where combination packages are used, and the inner packages are of glass, porcelain or stoneware, there must be sufficient inert cushoning material in contact with inner and outer packages are lose of glass, porcelain or stoneware, there must be sufficient inert cushoning material in contact with inner and outer packages unless the outer packaging is a close fitting moulded plastic box and the substances are not incompatible with the plastic. Phosphoric acid: is a medium-strong acid which produces violent reaction with bases may produce violent react when water is added to the concentrated form reacts violently with solutions containing ammonia or bleach, azo compounds, epoxides, amides, ammonia hydroxide, calcium oxide, cyanides, epidhordhydrin, esters, halogenated organics, isocyanates, ketones, oleum, organic anhydrides, sodium tetrabes util mixtures with nitromethane at elevated temperatures attacks many metals producing hydrogen gas at room temperature dees not attack stainless steel, copper or its alloys attacks glass, ceramics, and some plastics, rubber and contigns Inorganic acids are enarity soluble in water with the release of hyd
Suitable container	 DO NOT use aluminium or galvanised containers Check regularly for spills and leaks Lined metal can, lined metal pail/ can. Plastic pail. Polyliner drum. Packing as recommended by manufacturer. Check all containers are clearly labelled and free from leaks. For low viscosity materials Drums and jerricans must be of the non-removable head type. Where a can is to be used as an inner package, the can must have a screwed enclosure. For materials with a viscosity of at least 2580 cSt. (23 deg. C) and solids (between 15 C deg. and 40 deg C.): Removable head packaging; Cans with friction closures and low pressure tubes and cartridges may be used. Where a conits of the packages are used, and the inner packages are of glass, porcelain or stoneware, there must be sufficient inert cushioning material in contact with inner and outer packages unless the outer packaging is a close fitting moulded plastic box and the substances are not incompatible with the plastic. Phosphoric acid: is a medium-strong acid which produces violent reaction with bases is a medium-strong acid which produces violent reaction with bases is a medium-strong acid which produces violent reaction with bases is a medium-strong acid, strong oxides, alkanolarinines, alcohols, alkylene oxides, anides, ammonia, ammonia hydroxide, calcian oxide, cynides, spiholron/hydre, elikanolarinies, alcohols, alkylene oxides, medias, smonai, anythrides, sodium tetraborate, sulfuces, sulfuric acid; strong oxidiers, vinyl acetate forms eplosive mixtures with hitromethane at elevated temperatures attacks many metals producing hydrogen gas at arom temperature does not attack stainless steel, copper or it alloys atatoks glase, ceramics, and some plastics, rub
Suitable container	 DO NOT use aluminium or galvanised containers Check regularly for spills and leaks Lined metal can, lined metal pail/ can. Plastic pail. Polyliner drum. Packing as recommended by manufacturer. Check all containers are clearly labelled and free from leaks. For law viscosity materials Orums and jericans must be of the non-removable head type. Where a can is to be used as an inner package, the can must have a screwed enclosure. For metal swith a viscosity of at least 2500 cSt. (23 deg. C) and solids (between 15 C deg. and 40 deg C.): Removable head packaging; Cans with friction closures and I ow pressure tubes and cartridges may be used. Where combination packages are used, and the inner packages are of glass, porcelain or stoneware, there must be sufficient inert cushioning material in contact with inner and outer packages unless the outer packaging is a close fitting moulded plastic box and the substances are not incompatible with the plastic. Phosphoric acid: is a medium-strong acid which produces violent reaction with bases may poulde violent react when water is added to the concentrated form reacts violently with solutions containing ammonia or bleach, azo compounds, epoxides and other polymerisable compounds reacts violently with interrementa. at elevated temperatures attack many metals producing hydrogen gas at elevated temperatures attack sam yenes (scrept or its alloys at at com temperature does not attack stainless steel, copper or its alloys at at com temperature does not attack stainless steel, copper or its alloys at acoust the metal can, and some plastes, ruber and coating I horganic acids are generally soluble in water with the release of hydrogen ions. The resulting solutions have pt⁴s of less than 7.0. Inorganic acids are generally soluble

Control parameters

Occupational Exposure Limits (OEL)

SourceIngredientMaterial nameTWASTELPeakNotesNew Zealand Workplace Exposure Standards (WES)phosphoric acidPhosphoric acid1 mg/m3Not AvailableNot AvailableNot AvailableNew Zealand Workplace Exposure Standards (WES)dipropylene glycol monomethyl etherDipropylene glycol methyl ether100 ppm / 606 mg/m3909 mg/m3 / 150 ppmNot Available(skin) - Skin absorption	INGREDIENT DATA									
New Zealand Workplace Exposure Standards (WES)phosphoric acidPhosphoric acid1 mg/m3Not AvailableNot AvailableNot AvailableNew Zealand Workplace Exposure Standards (WES)dipropylene glycol monomethyl etherDipropylene glycol methyl ether100 ppm / 606 mg/m3909 mg/m3 / 150 ppmNot AvailableNot Available	Source	Ingredient	Material nam	ne	TWA		STEL		Peak	Notes
New Zealand Workplace dipropylene glycol Dipropylene glycol 100 ppm / 606 909 mg/m3 / 150 Not (skin) - Skin Exposure Standards (WES) monomethyl ether methyl ether mg/m3 ppm Available absorption	New Zealand Workplace Exposure Standards (WES)	phosphoric acid	Phosphoric a	cid	1 mg/m3	3	Not Availab	ble	Not Available	Not Available
	New Zealand Workplace Exposure Standards (WES)	dipropylene glycol monomethyl ether	Dipropylene g methyl ether	glycol	100 ppn mg/m3	n / 606	909 mg/m3 ppm	8 / 150	Not Available	(skin) - Skin absorption
Emergency Limits	Emergency Limits									
Ingredient TEEL-1 TEEL-2 TEEL-3	Ingredient	TEEL-1		TEEL-2		TEEL-3				
phosphoric acid Not Available Not Available Not Available	phosphoric acid	Not Available		Not Available		Not Av	Not Available			
dipropylene glycol monomethyl ether 150 ppm 1700* ppm 9900** ppm	dipropylene glycol monomethyl ether	150 ppm		1700* ppm				9900**	ppm	
benediest Ocident IDU										
ingreaient Original IDLH Revised IDLH	Ingredient					Revised	IDLH			
phosphoric acid 1,000 mg/m3 Not Available	phosphoric acid	1,000 mg/m3				Not Available				
dipropylene glycol monomethyl ether 600 ppm Not Available	dipropylene glycol monomethyl ether	600 ppm				Not Avail	able			
water Not Available Not Available	water	Not Available				Not Avail	able			

MATERIAL DATA

Exposure controls

	Engineering controls are used to remove a hazard or place a barrier between the worker and the hazard. Well-designed engineering controls can be highly effective in protecting workers and will typically be independent of worker interactions to provide this high level of protection. The basic types of engineering controls are: Process controls which involve changing the way a job activity or process is done to reduce the risk. Enclosure and/or isolation of emission source which keeps a selected hazard "physically" away from the worker and ventilation that strategically "adds" and "removes" air in the work environment. Ventilation can remove or dilute an air contaminant if designed properly. The design of a ventilation system must match the particular process and chemical or contaminant in use. Employers may need to use multiple types of controls to prevent employee overexposure. Local exhaust ventilation usually required. If risk of overexposure exists, wear approved respirator. Correct fit is essential to obtain adequate protection. An approved self contained breathing apparatus (SCBA) may be required in some situations. Provide adequate ventilation in warehouse or closed storage area. Air contaminants generated in the workplace possess varying "escape" velocities which, in turn, determine the "capture velocities" of fresh circulating air required to effectively remove the contaminant. Type of Contaminant:				
	solvent, vapours, degreasing etc., evaporating from tank (in	n still air).	0.25-0.5 m/s (50- 100 f/min.)		
Appropriate engineering	aerosols, fumes from pouring operations, intermittent conta spray drift, plating acid fumes, pickling (released at low vel	iner filling, low speed conveyer transfers, welding, ocity into zone of active generation)	0.5-1 m/s (100- 200 f/min.)		
controls	direct spray, spray painting in shallow booths, drum filling, generation into zone of rapid air motion)	conveyer loading, crusher dusts, gas discharge (active	1-2.5 m/s (200- 500 f/min.)		
	grinding, abrasive blasting, tumbling, high speed wheel ger of very high rapid air motion).	2.5-10 m/s (500- 2000 f/min.)			
	Within each range the appropriate value depends on:				
	Lower end of the range Upper end of the range				
	1: Room air currents minimal or favourable to capture 1: Disturbing room air currents				
	2: Contaminants of low toxicity or of nuisance value only.	2: Contaminants of high toxicity			
	3: Intermittent, low production. 3: High production, heavy use				
	4: Large hood or large air mass in motion 4: Small hood-local control only				
	Simple theory shows that air velocity falls rapidly with distance away from the opening of a simple extraction pipe. Velocity generally decreases with the square of distance from the extraction point (in simple cases). Therefore the air speed at the extraction point should be adjusted, accordingly, after reference to distance from the contaminating source. The air velocity at the extraction fan, for example, should be a minimum of 1-2 m/s (200-400 f/min) for extraction of solvents generated in a tank 2 meters distant from the extraction point. Other mechanical considerations, producing performance deficits within the extraction apparatus, make it essential that theoretical air velocities are multiplied by factors of 10 or more when extraction systems are installed or used.				
Individual protection measures, such as personal protective equipment					
Eye and face protection	 Safety glasses with unperforated side shields may be used where continuous eye protection is desirable, as in laboratories; spectacles are not sufficient where complete eye protection is needed such as when handling bulk-quantities, where there is a danger of splashing or if the material may be under pressure. Chemical goggles. Whenever there is a danger of the material coming in contact with the eyes; goggles must be properly fitted. [AS/NZ 1337.1, EN166 or national equivalent] Full face shield (20 cm, 8 in minimum) may be required for supplementary but never for primary protection of eyes; these afford face protection. Alternatively a gas mask may replace splash goggles and face shields. Contact lenses may pose a special hazard; soft contact lenses may absorb and concentrate irritants. A written policy document, describing the wearing of lenses or restrictions on use, should be created for each workplace or task. This should include a review of lens absorption and adsorption for the class of chemicals in use and an account of injury experience. Medical and first-aid personnel should be trained in their removal and suitable equipment should be readily available. In the event of chemical exposure, begin eye irrigation immediately and remove contact lens as soon as practicable. Lens should be removed at the first signs of eye redness or 				

	irritation - lens should be removed in a clean environment only after workers have washed hands thoroughly. [CDC NIOSH Current Intelligence Bulletin 59].
Skin protection	See Hand protection below
Hands/feet protection	 Elbow length PVC gloves When handling corrosive liquids, wear trousers or overalls outside of boots, to avoid spills entering boots. The selection of suitable gloves does not only depend on the material, but also on further marks of quality which vary from manufacturer to manufacturer. Where the chemical is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. The selection of suitable gloves does not only depend on the material, but also on further marks of quality which vary from manufacturer to manufacturer. Where the chemical is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. The exact break through time for substances has to be obtained from the manufacturer of the protective gloves and has to be observed when making a final choice. Personal hygiene is a key element of effective hand care. Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. Suitability and durability of glove type is dependent on usage. Important factors in the selection of gloves include: frequency and duration of contact, chemical repeated contact may occur, a glove with a protection class of 5 or higher (breakthrough time greater than 240 minutes according to EN 374, ASIN2S 2161.10 or national equivalent) is recommended. When only brief contact is expected, a glove with a protection class of 3 or higher (breakthrough time greater than 60 minutes according to EN 374, ASIN2S 2161.10 or national equivalent). When only brief contact is expected, a glove with a protection class of 3 or higher (breakthrough time seconding to EN 3
Body protection	See Other protection below
Other protection	 Overalls. PVC Apron. PVC protective suit may be required if exposure severe. Eyewash unit. Ensure there is ready access to a safety shower.

Recommended material(s)

GLOVE SELECTION INDEX

Glove selection is based on a modified presentation of the:

"Forsberg Clothing Performance Index".

The effect(s) of the following substance(s) are taken into account in the *computer-generated* selection:

RESTOFINISH RusGo

Material	CPI
NEOPRENE	A
BUTYL	С
NAT+NEOPR+NITRILE	С
NATURAL RUBBER	С
NATURAL+NEOPRENE	С
NEOPRENE/NATURAL	С
NITRILE	С
NITRILE+PVC	С
PE	С
PVA	С
PVC	С
SARANEX-23	С
VITON	С

* CPI - Chemwatch Performance Index

A: Best Selection

B: Satisfactory; may degrade after 4 hours continuous immersion

C: Poor to Dangerous Choice for other than short term immersion NOTE: As a series of factors will influence the actual performance of the glove, a final election must be been deer detailed chearaction

selection must be based on detailed observation. -* Where the glove is to be used on a short term, casual or infrequent basis, factors

such as "feel" or convenience (e.g. disposability), may dictate a choice of gloves which

Respiratory protection

Type AB-P Filter of sufficient capacity. (AS/NZS 1716 & 1715, EN 143:2000 & 149:2001, ANSI Z88 or national equivalent)

Where the concentration of gas/particulates in the breathing zone, approaches or exceeds the "Exposure Standard" (or ES), respiratory protection is required. Degree of protection varies with both face-piece and Class of filter; the nature of protection varies with Type of filter.

Required Minimum Protection Factor	Half-Face Respirator	Full-Face Respirator	Powered Air Respirator
up to 10 x ES	AB-AUS P2	-	AB-PAPR-AUS / Class 1 P2
up to 50 x ES	-	AB-AUS / Class 1 P2	-
up to 100 x ES	-	AB-2 P2	AB-PAPR-2 P2 ^

^ - Full-face

 $\begin{array}{l} \mathsf{A}(\mathsf{All \ classes}) = \mathsf{Organic \ vapours, \ B \ AUS \ or \ B1} = \mathsf{Acid \ gasses, \ B2} = \mathsf{Acid \ gas \ or} \\ \mathsf{hydrogen \ cyanide(HCN), \ B3} = \mathsf{Acid \ gas \ or} \ hydrogen \ cyanide(HCN), \ E = \mathsf{Sulfur} \\ \mathsf{dioxide}(\mathsf{SO2}), \ G = \mathsf{Agricultural \ chemicals, \ K} = \mathsf{Ammonia}(\mathsf{NH3}), \ \mathsf{Hg} = \mathsf{Mercury, \ NO} = \\ \mathsf{Oxides \ of \ nitrogen, \ MB} = \mathsf{Methyl \ bromide, \ AX} = \mathsf{Low \ boiling \ point \ organic \ compounds(below \ 65 \ degC)} \end{array}$

- Cartridge respirators should never be used for emergency ingress or in areas of unknown vapour concentrations or oxygen content.
- The wearer must be warned to leave the contaminated area immediately on detecting any odours through the respirator. The odour may indicate that the mask is not functioning properly, that the vapour concentration is too high, or that the mask is not properly fitted. Because of these limitations, only restricted use of cartridge respirators is considered appropriate.
- Cartridge performance is affected by humidity. Cartridges should be changed after
 2 hr of continuous use unless it is determined that the humidity is less than 75%, in which case, cartridges can be used for 4 hr. Used cartridges should be discarded daily, regardless of the length of time used

might otherwise be unsuitable following long-term or frequent use. A qualified practitioner should be consulted.

Ansell Glove Selection

Glove — In order of recommendation			
AlphaTec 02-100			
AlphaTec® Solvex® 37-185			
AlphaTec® 58-008			
AlphaTec® 58-530B			
AlphaTec® 58-530W			
AlphaTec® 58-735			
AlphaTec® 79-700			
AlphaTec® Solvex® 37-675			
AlphaTec® 38-612			
DermaShield™ 73-711			

The suggested gloves for use should be confirmed with the glove supplier.

SECTION 9 Physical and chemical properties

Information on basic physical and chemical properties

Appearance	Clear to brown liquid with mild ethereal odour; mixes with water.		
Physical state	Liquid	Relative density (Water = 1)	1.10-1.11
Odour	Not Available	Partition coefficient n-octanol / water	Not Available
Odour threshold	Not Available	Auto-ignition temperature (°C)	Not Applicable
pH (as supplied)	1-2	Decomposition temperature (°C)	Not Available
Melting point / freezing point (°C)	Not Available	Viscosity (cSt)	Not Available
Initial boiling point and boiling range (°C)	110	Molecular weight (g/mol)	Not Applicable
Flash point (°C)	Not Applicable	Taste	Not Available
Evaporation rate	Not Available	Explosive properties	Not Available
Flammability	Not Applicable	Oxidising properties	Not Available
Upper Explosive Limit (%)	Not Applicable	Surface Tension (dyn/cm or mN/m)	Not Available
Lower Explosive Limit (%)	Not Applicable	Volatile Component (%vol)	85
Vapour pressure (kPa)	Not Available	Gas group	Not Available
Solubility in water	Miscible	pH as a solution (1%)	Not Available
Vapour density (Air = 1)	Not Available	VOC g/L	Not Available

SECTION 10 Stability and reactivity

Reactivity	See section 7
Chemical stability	 Contact with alkaline material liberates heat Unstable in the presence of incompatible materials. Product is considered stable. Hazardous polymerisation will not occur.
Possibility of hazardous reactions	See section 7
Conditions to avoid	See section 7
Incompatible materials	See section 7
Hazardous decomposition products	See section 5

SECTION 11 Toxicological information

nformation on toxicological effects				
Information on toxicological ef	Acidic corrosives produce respiratory tract irritation with coughing, choking and mucous membrane damage. Symptoms of exposure may include dizziness, headache, nausea and weakness. In more severe exposures, pulmonary oedema may be evident either immediately or after a latent period of 5-72 hours. Symptoms of pulmonary oedema include a tightness in the chest, dyspnoea, frothy sputum and cyanosis. Examination may reveal hypotension, a weak and rapid pulse and moist rates. Death, due to anoxia, may occur several hours after onset of the pulmonary oedema. Inhalation of vapours may cause drowsiness and dizziness. This may be accompanied by narcosis, reduced alertness, loss of reflexes, lack of coordination and vertigo. In fog-laden atmospheres rats exposed to dipropylene glycol monomethyl ether DPME, for 7 hours, exhibited a mild narcosis from which they rapidly recovered. Controlled human exposures to vapour produced CNS impairment at 1000 ppm in one subject			
	Inhalation of phosphoric acid vapour or mist may cause choking, coughing, headache, weakness and dizziness. Prolonged or repeated inhalation of vapour or mist may cause pulmonary oedema (lung damage) and cyanosis			

	Line e lesse solution activity			
	Relatively small amounts absorbed from the lungs may prove fatal. Exposure to high concentrations causes bronchitis and is characterised by the onset of haemorrhagic pulmonary oedema.			
	Accidental ingestion of the material may be harmful; animal experim produce serious damage to the health of the individual.	nents indicate that ingestion of less than 150 gram may be fatal or may		
Ingestion	Ingestion of acidic corrosives may produce circumoral burns with a and oesophagus. Immediate pain and difficulties in swallowing and respiratory distress and possibly, asphyxia. Nausea, vomiting, diarrh produce a vomitus containing fresh or dark blood and large shreds or shallow respiration and clammy skin may be symptomatic of the exp Severe cases may show gastric and oesophageal perforation with p gastric and pyloric sphincter may occur as within several weeks or r asphyxia, circulatory collapse or aspiration of even minute amounts pneumonia. Coma and convulsions may be terminal. Phosphates are slowly and incompletely absorbed from the gastroir systemic effects which occur when introduced by other routes. Such pressure, slow pulse, cyanosis, carpal spasm, coma and tetany. The Ingestion of large amounts of phosphate salts (over 1 gm for an adu abdominal cramp. Large doses (4-8 gm) will almost certainly produc excreted in the faeces of healthy individuals without producing syste Ingestion of large quantity of phosphoric acid may cause severe abor shock and death. Although less hazardous than nitric and sulfuric acid, phosphoric acid phosphoric acid phosphoric acid phosphorie acid phosphoric acid phosphoric ac	distinct discolouration of the mucous membranes of the mouth, throat speaking may also be evident. Oedema of the epiglottis may produce hoea and a pronounced thirst may occur. More severe exposures may of mucosa. Shock, with marked hypotension, weak and rapid pulse, posure. Circulatory collapse may, if left untreated, result in renal failure. beitonitis, fever and abdominal rigidity. Stricture of the oesophageal, may be delayed for years. Death may be rapid and often results from . Delayed deaths may be due to peritonitis, severe nephritis or htestinal tract and are unlikely (other than in abuse) to produce the n effects include vomiting, lethargy, fever, diarrhoea, falls in blood ese effects result following sequestration of blood calcium. ult) may produce osmotic catharsis resulting in diarrhoea and probably, ce these effects in most individuals. Most of the ingested salt will be emic toxicity. Doses in excess of 10 gm may produce systemic toxicity. dominal pains, thirst, acidaemia, difficult breathing, convulsions, collapse, cid has equal corrosive action upon ingestion. Death of an individual 19		
	days after ingestion of phosphoric acid was due to recurrent interna pancreas was evident at autopsy.	I haemorrhage. Necrosis of the upper and lower digestive tract and		
Skin Contact	 Skin contact with acidic corrosives may result in pain and burns; these may be deep with distinct edges and may heal slowly with the formation of scar tissue. Skin contact with the material may damage the health of the individual; systemic effects may result following absorption. Open cuts, abraded or irritated skin should not be exposed to this material Entry into the blood-stream through, for example, cuts, abrasions, puncture wounds or lesions, may produce systemic injury with harmful effects. Examine the skin prior to the use of the material and ensure that any external damage is suitably protected. Continuous contact with DPME of the skin of numerous rabbits for 90 days caused only slight scaliness. Patch tests on human volunteers produced no evidence of primary irritation or sensitisation. Sufficient absorption did occur in rabbits to produce narcosis and high doses proved lethal. Pathology revealed gastric distension, occasional gastric irritation and granular and hydropic changes to kidneys The material produces severe skin irritation; evidence exists, or practical experience predicts, that the material either: produces significant and severe inflammation when applied to the healthy intact skin of animals (for up to four hours), such inflammation being present twenty-four hours or more after the end of the exposure period. Skin irritation may also be present after prolonged or repeated exposure; this may result in a form of contact dermatitis (nonallergic). The dermatitis is often characterised by skin redness (erythema) and swelling (oedema) which may progress to blistering (vesiculation), scaling and thickening of the epidermis. At the microscopic level there may be intercellular oedema of the spongy layer of the skin (spongiosis) and intracellular oedema of the epidermis. 			
	Direct eye contact with acid corrosives may produce pain, lachryma	tion, photophobia and burns. Mild burns of the epithelia generally recover		
Eye	rapidly and completely. Severe burns produce long-lasting and possible irreversible damage. The appearance of the burn may not be apparent for several weeks after the initial contact. The cornea may ultimately become deeply vascularised and opaque resulting in blindness. When applied to the eye(s) of animals, the material produces severe ocular lesions which are present twenty-four hours or more after instillation. When one drop of undiluted dipropylene glycol monomethyl ether (DPME) was placed in a rabbits eyes on each of five consecutive days, a mild transitory irritation of the conjunctival membranes occurred. Fluorescein staining revealed no corneal damage. Direct contact of the substance can produce painful irritation (blepharoconjunctivitis, slight keratitis, and an increase in intra-ocular pressure) which, is however rapidly reversible. Persistent eye lesions do not develop			
Chronic	Repeated or prolonged exposure to acids may result in the erosion of teeth, inflammatory and ulcerative changes in the mouth and necrosis (rarely) of the jaw. Bronchial irritation, with cough, and frequent attacks of bronchial pneumonia may ensue. Gastrointestinal disturbances may also occur. Chronic exposures may result in dermatitis and/or conjunctivitis. The impact of inhaled acidic agents on the respiratory tract depends upon a number of interrelated factors. These include physicochemical characteristics, e.g., gas versus aerosol; particle size (small particles can penetrate deeper into the lung); water solubility (more soluble agents are more likely to be removed in the nose and mouth). Given the general lack of information on the particle size of aerosols involved in occupational exposures to acids, it is difficult to identify their principal deposition site within the respiratory tract. Acid mists containing particles with a diameter of up to a few micrometers will be deposited in both the upper and lower airways. They are irritating to muccus epithelia, they cause dental erosion, and they produce acute effects in the lungs (symptoms and changes in pulmonary function). Asthmatics appear to be at particular risk for pulmonary effects. Limited evidence suggests that repeated or long-term occupational exposure may produce cumulative health effects involving organs or biochemical systems. Rats, rabbits, guinea pigs and monkeys exposed to DPME, 7 hr/day, 5 days a week for periods of 6-8 months to saturated atmospheres (300 ppm), exhibited little effect. Narcotic effects were produced in rats. This concentration of vapour is objectionable to human beings.			
	disseminated atrophy of the proximal tubule. Animals fed on sodium and long-term studies, showed increased bone porosity; hyperparat Long-term exposure to respiratory irritants may result in disease of f	n phosphate dibasic and potassium dihydrogen phosphate, in both short- thyroidism and soft tissue calcification were also evident. the airways involving difficult breathing and related systemic problems.		
	тохісіту	IRRITATION		
RESTOFINISH RusGo	Not Available	Not Available		
	τοχιςιτγ	IRRITATION		
	Dermal (rabbit) LD50: >1260 mg/kg ^[2]	Eye (rabbit): 119 mg - SEVERE [Monsanto]*		
phosphoric acid	Inhalation (Rat) LC50: 0.026 mg/L4h ^[2]	Eye: adverse effect observed (irritating) ^[1]		
	Oral (Rat) LD50: 1530 mg/kg ^[2]	Skin (rabbit):595 mg/24h - SEVERE		

Skin: adverse effect observed (corrosive)^[1]

	τοχιςιτγ	IRRITATION		
	Dermal (rabbit) LD50: 9500 mg/kg ^[2]	Eye (human): 8 mg - mild		
	Oral (Rat) LD50: 5135 mg/kg ^[2]	Eye (rabbit): 500 mg/24hr - mild		
dipropylene glycol monomethyl ether		Eye: no adverse effect observed (not irritating) ^[1]		
		Skin (rabbit): 238 mg - mild		
		Skin (rabbit): 500 mg (open)-mild		
		Skin: no adverse effect observed (not irritating) ^[1]		
	ΤΟΧΙΟΙΤΥ	IRRITATION		
water	Oral (Rat) LD50: >90000 mg/kg ^[2]	Not Available		
Legend:	1. Value obtained from Europe ECHA Registered Substances - Acu specified data extracted from RTECS - Register of Toxic Effect of c	Ite toxicity 2. Value obtained from manufacturer's SDS. Unless otherwise hemical Substances		
PHOSPHORIC ACID	 phosphoric acid (85%) for acid mists, aerosols, vapours Data from assays for genotoxic activity in vitro suggest that eukaryotic cells are susceptible to genetic damage when the pH falls to about 6.5. Cells from the respiratory tract have not been examined in this respect. Mucous secretion may protect the cells of the airways from direct exposure to inhaled acidic mists, just as mucous plays an important role in protecting the gastric epithelium from its auto-secreted hydrochloric acid. In considering whether pH itself induces genotoxic events in vivo in the respiratory system, comparison should be mac with the human stomach, in which gastric juice may be at pH 1-2 under fasting or noctural conditions, and with the human urinary bladc in which the pH of urine can range from <5 to > 7 and normally averages 6.2. Furthermore, exposures to low pH in vivo differ from expose <i>in vitro</i> in that, <i>in vivo</i>, only a portion of the cell surface is subjected to the adverse conditions, so that perturbation of intracellular homeostasis may be maintained more readily than in vitro. 			
	The material may produce severe irritation to the eye causing prono produce conjunctivitis. The material may produce severe skin irritation after prolonged or n This form of dermatitis is often characterised by skin redness (eryth Histologically there may be intercellular oedema of the spongy laye contact is unlikely, given the severity of response, but repeated exp	punced inflammation. Repeated or prolonged exposure to irritants may epeated exposure, and may produce a contact dermatitis (nonallergic). ema) thickening of the epidermis. r (spongiosis) and intracellular oedema of the epidermis. Prolonged osures may produce severe ulceration.		
DIPROPYLENE GLYCOL MONOMETHYL ETHER	The material may produce seven skin initiation after prolonged or repeated exposure, and may produce a contact demaititis (nonallergic). This form of demaintis is often characterised by skin redness (erythem) hitchening of the apidemis. Histologically there may be intercellular cedema of the spongy layer (spongiosis) and intracellular cedema of the epidemis. Prolonged of the sevenity of response, but repeated exposures may produce severe ulceration. For propylene glycol ethers include propylene glycol n-butyl ether (PB); dipropylene glycol heat (DPB); dipropylene glycol ethers in schwer glycol ethers include propylene glycol in-butyl ether (PB); dipropylene glycol ethers has now ether series. The common toxicities associated with the lower molecular weight thomologues of the ethylene series. The common toxicities associated with the lower molecular weight thomologues of the ethylene series. The common toxicities associated with the lower molecular weight thomologues in the subject series. The common toxicities associated with the come molecular weight thomologues in the subject series. The common toxicities associated with the come molecular weight thomologues in the subject series. The common toxicities associated with the come and the series are not allower to the series are not allower to the social terminal thydroxy (group produces an alkoxyacetic acid. The reproductive and developmental toxities of the subject series are allowed to the series are not allower toxicity to the cancel and the propylene glycol-based (and no material grade propylene glycol-based (and possibly hermolytic effects). This alpha isomer comprises grader than glys of the isomer instruer in the commercial grade propylene glycol-based (and on material grade glycol ether presents a low toxicity hazard. PGEs, whether mono, di- or tripropylene glycol alters is propylene glycol alters is propylene glycol alters is propylene glycol wheth is the stock of the grader presents as toxicity brazerd. PGEs, whether mono, di- or tripropylene glycol al			

	The weight of the evidence indicates that propylene glycol ethers are not likely to be genotoxic. <i>In vitro</i> , negative results have been seen in a number of assays for PnB, DPMB, DPMA and TPM. Positive results were only seen in 3 out of 5 chromosome aberration assays in mammalian cells with DPnB. However, negative results were seen in a mouse micronucleus assay with DPnB and PM. Thus, there is no evidence to suggest these PGEs would be genotoxic <i>in vivo</i> . In a 2-year bioassay on PM, there were no statistically significant increases in tumors in rats and mice. The material may be irritating to the eye, with prolonged contact causing inflammation. Repeated or prolonged exposure to irritants may produce conjunctivitis. The material may cause skin irritation after prolonged or repeated exposure and may produce a contact dermatitis (nonallergic). This form of dermatitis is often characterised by skin redness (erythema) and swelling epidermis. Histologically there may be intercellular oedema of the epidermis.		
PHOSPHORIC ACID & WATER	No significant acute toxicological data identified in liter	ature search.	
PHOSPHORIC ACID & DIPROPYLENE GLYCOL MONOMETHYL ETHER	Asthma-like symptoms may continue for months or even years after exposure to the material ends. This may be due to a non-allergic condition known as reactive airways dysfunction syndrome (RADS) which can occur after exposure to high levels of highly irritating compound. Main criteria for diagnosing RADS include the absence of previous airways disease in a non-atopic individual, with sudden onset of persistent asthma-like symptoms within minutes to hours of a documented exposure to the irritant. Other criteria for diagnosis of RADS include the absence of previous airways disease in a non-atopic individual, with sudden onset of persistent asthma-like symptoms within minutes to hours of a documented exposure to the irritant. Other criteria for diagnosis of RADS include a reversible airflow pattern on lung function tests, moderate to severe bronchial hyperreactivity on methacholine challenge testing, and the lack of minimal lymphocytic inflammation, without eosinophilia. RADS (or asthma) following an irritating inhalation is an infrequent disorder with rates related to the concentration of and duration of exposure to the irritating substance. On the other hand, industrial bronchitis is a disorder that occurs as a result of exposure due to high concentrations of irritating substance (often particles) and is completely reversible after exposure ceases. The disorder is characterized by difficulty breathing, cough and mucus production.		
Acute Toxicity	✓	Carcinogenicity	×
Skin Irritation/Corrosion	×	Reproductivity	×
Serious Eye Damage/Irritation	*	STOT - Single Exposure	×
Respiratory or Skin sensitisation	×	STOT - Repeated Exposure	×
Mutagenicity	×	Aspiration Hazard	×
		Legend: X – Data either not V – Data available t	available or does not fill the criteria for classification o make classification

SECTION 12 Ecological information

	Endpoint	Test Duration (hr)	Species	Value	Source
RESTOFINISH RusGo	Not Available	Not Available	Not Available	Not Available	Not Availabl
	Endpoint	Test Duration (hr)	Species	Value	Sourc
	EC50	72h	Algae or other aquatic plants	77.9mg/l	2
nhosphoric acid	EC50	48h	Crustacea	>100mg/l	2
	LC50	96h	Fish	67.94- 113.76mg/L	4
	NOEC(ECx)	72h	Algae or other aquatic plants	<7.5mg/l	2
	Endpoint	Test Duration (hr)	Species	Value	Sourc
	EC50	72h	Algae or other aquatic plants	>969mg/l	2
dipropylene glycol	EC50	48h	Crustacea	1930mg/l	2
monomethyl ether	LC50	96h	Fish	>1000mg/l	2
	NOEC(ECx)	528h	Crustacea	>=0.5mg/l	2
	EC50	96h	Algae or other aquatic plants	>969mg/l	2
	Endpoint	Test Duration (hr)	Species	Value	Source
water	Not Available	Not Available	Not Available	Not Available	Not Availab

DO NOT discharge into sewer or waterways.

Persistence and degradability

Ingredient	Persistence: Water/Soil	Persistence: Air
phosphoric acid	HIGH	HIGH
dipropylene glycol monomethyl ether	HIGH	нідн
water	LOW	LOW

Bioaccumulative potential

Ingredient	Bioaccumulation
phosphoric acid	LOW (LogKOW = -0.7699)
dipropylene glycol monomethyl ether	LOW (BCF = 100)

Mobility in soil

Ingredient	Mobility
phosphoric acid	HIGH (Log KOC = 1)
dipropylene glycol monomethyl ether	LOW (Log KOC = 10)

SECTION 13 Disposal considerations

Waste treatment methods	
Product / Packaging disposal	 Containers may still present a chemical hazard/ danger when empty. Return to supplier for reuse/ recycling if possible. Otherwise: If container can not be cleaned sufficiently well to ensure that residuals do not remain or if the container cannot be used to store the same product, then puncture containers, to prevent re-use, and bury at an authorised landfill. Where possible retain label warnings and SDS and observe all notices pertaining to the product. Legislation addressing waste disposal requirements may differ by country, state and/ or territory. Each user must refer to laws operating in their area. In some areas, certain wastes must be tracked. A Hierarchy of Controls seems to be common - the user should investigate: Reduction Reuse Recycling Disposal (if all else fails) This material may be recycled if unused, or if it has not been contaminated so as to make it unsuitable for its intended use. If it has been contaminated, it may be possible to reclaim the product by filtration, distillation or some other means. Shelf life considerations should also be applied in making decisions of this type. Note that properties of a material may change in use, and recycling or reuse may not always be appropriate. Do NOT allow wash water from cleaning or process equipment to enter drains. It may be necessary to collect all wash water for treatment before disposal. In all cases disposal to sever may be subject to local laws and regulations and these should be considered first. Where in doubt contact the responsible authority. Recycle wherever possible. Consult manufacturer for recycling options or consult local or regional waste management authority for disposal if no suitable treatment or disposal field ligencilcally licensed to accept chemical and / or pharmaceutical wastes or Incineration in a licensed apparatus (after admixture with suitable combustible mate

Ensure that the hazardous substance is disposed in accordance with the Hazardous Substances (Disposal) Notice 2017

Disposal Requirements

Packages that have been in direct contact with the hazardous substance must be only disposed if the hazardous substance was appropriately removed and cleaned out from the package. The package must be disposed according to the manufacturer's directions taking into account the material it is made of. Packages which hazardous content have been appropriately treated and removed may be recycled.

The hazardous substance must only be disposed if it has been treated by a method that changed the characteristics or composition of the substance and it is no longer hazardous.

Only dispose to the environment if a tolerable exposure limit has been set for the substance.

Only deposit the hazardous substance into or onto a landfill or sewage facility or incinerator, where the hazardous substance can be handled and treated appropriately.

SECTION 14 Transport information

Labels Required



1805

Marine Pollutant	NO
HAZCHEM	2R

Land transport (UN)

14.1. UN number or ID number	1805	805	
14.2. UN proper shipping name	PHOSPHORIC ACID,	HOSPHORIC ACID, SOLUTION	
14.3. Transport hazard class(es)	Class Subsidiary Hazard	8 Not Applicable	
14.4. Packing group	Ш		
14.5. Environmental hazard	Not Applicable		
14.6. Special precautions for user	Special provisions	223 5 L	

Air transport (ICAO-IATA / DGR)

14.2. UN proper shipping name	Phosphoric acid, solution			
14.3. Transport hazard class(es)	ICAO/IATA Class ICAO / IATA Subsidiary Hazard ERG Code	8 Not Applicable 8L		
14.4. Packing group		1		
14.5. Environmental hazard	Not Applicable			
14.6. Special precautions for user	Special provisions Cargo Only Packing Instructions Cargo Only Maximum Qty / Pack Passenger and Cargo Packing Instructions Passenger and Cargo Maximum Qty / Pack Passenger and Cargo Limited Quantity Packing Instructions Passenger and Cargo Limited Maximum Qty / Pack		A3 A803 856 60 L 852 5 L Y841 1 L	

Sea transport (IMDG-Code / GGVSee)

14.1. UN number	1805			
14.2. UN proper shipping name	PHOSPHORIC ACID S	PHOSPHORIC ACID SOLUTION		
14.3. Transport hazard class(es)	IMDG Class IMDG Subsidiary Ha	8 zard Not Applicable		
14.4. Packing group	Ш			
14.5 Environmental hazard	Not Applicable			
14.6. Special precautions for user	EMS Number Special provisions Limited Quantities	F-A, S-B 223 5 L		

14.7.1. Transport in bulk according to Annex II of MARPOL and the IBC code Not Applicable

14.7.2. Transport in bulk in accordance with MARPOL Annex V and the IMSBC Code

Product name	Group
phosphoric acid	Not Available
dipropylene glycol monomethyl ether	Not Available
water	Not Available

14.7.3. Transport in bulk in accordance with the IGC Code

Product name	Ship Type
phosphoric acid	Not Available
dipropylene glycol monomethyl ether	Not Available
water	Not Available

SECTION 15 Regulatory information

Safety, health and environmental regulations / legislation specific for the substance or mixture

This substance is to be managed using the conditions specified in an applicable Group Standard

HSR Number	Group Standard
HSR100425	Pharmaceutical Active Ingredients Group Standard 2020
HSR100756	Active Ingredients for Use in the Manufacture of Agricultural Compounds Group Standard 2020

Please refer to Section 8 of the SDS for any applicable tolerable exposure limit or Section 12 for environmental exposure limit.

phosphoric acid is found on the following regulatory lists

New Zealand Approved Hazardous Substances with controls

New Zealand Hazardous Substances and New Organisms (HSNO) Act - Classification of Chemicals

New Zealand Hazardous Substances and New Organisms (HSNO) Act - Classification of Chemicals - Classification Data

New Zealand Inventory of Chemicals (NZIoC)

New Zealand Workplace Exposure Standards (WES)

dipropylene glycol monomethyl ether is found on the following regulatory lists

New Zealand Hazardous Substances and New Organisms (HSNO) Act - Classification of Chemicals

New Zealand Hazardous Substances and New Organisms (HSNO) Act - Classification of Chemicals - Classification Data

New Zealand Inventory of Chemicals (NZIoC)

New Zealand Workplace Exposure Standards (WES)

water is found on the following regulatory lists

New Zealand Inventory of Chemicals (NZIoC)

Additional Regulatory Information

Not Applicable

Hazardous Substance Location

Subject to the Health and Safety at Work (Hazardous Substances) Regulations 2017.

Hazard Class	Quantity (Compliance Certificate)	Quantity (Compliance Certificate - Farms >4 ha)
8.2A	50 kg or 50 L	500 kg or 500 L

Certified Handler

Subject to Part 4 of the Health and Safety at Work (Hazardous Substances) Regulations 2017.

Not Applicable Not Applicable	

Refer Group Standards for further information

Maximum quantities of certain hazardous substances permitted on passenger service vehicles

Subject to Regulation 13.14 of the Health and Safety at Work (Hazardous Substances) Regulations 2017.

Hazard Class	Gas (aggregate water capacity in mL)	Liquid (L)	Solid (kg)	Maximum quantity per package for each classification
8.2A	prohibited	prohibited	prohibited	

Tracking Requirements

Not Applicable

National Inventory Status

National Inventory	Status
Australia - AIIC / Australia Non- Industrial Use	Yes
Canada - DSL	Yes
Canada - NDSL	No (phosphoric acid; dipropylene glycol monomethyl ether; water)
China - IECSC	Yes
Europe - EINEC / ELINCS / NLP	Yes
Japan - ENCS	Yes
Korea - KECI	Yes
New Zealand - NZIoC	Yes
Philippines - PICCS	Yes
USA - TSCA	Yes
Taiwan - TCSI	Yes
Mexico - INSQ	Yes
Vietnam - NCI	Yes
Russia - FBEPH	Yes
Legend:	Yes = All CAS declared ingredients are on the inventory No = One or more of the CAS listed ingredients are not on the inventory. These ingredients may be exempt or will require registration.

SECTION 16 Other information

Revision Date	10/06/2022
Initial Date	10/06/2022

SDS Version Summary

Version	Date of Update	Sections Updated
2.1	10/06/2022	Toxicological information - Chronic Health, Firefighting measures - Fire Fighter (fire incompatibility), Handling and storage - Handling Procedure, Composition / information on ingredients - Ingredients, Accidental release measures - Spills (major), Identification of the substance / mixture and of the company / undertaking - Supplier Information, Identification of the substance / mixture and of the company / undertaking - Synonyms, Name
2.2	14/08/2024	Identification of the substance / mixture and of the company / undertaking - Synonyms

Other information

Classification of the preparation and its individual components has drawn on official and authoritative sources as well as independent review by the Chemwatch Classification committee using available literature references.

The SDS is a Hazard Communication tool and should be used to assist in the Risk Assessment. Many factors determine whether the reported Hazards are Risks in the workplace or other settings. Risks may be determined by reference to Exposures Scenarios. Scale of use, frequency of use and current or available engineering controls must be considered.

end of SDS

RESTOFINISH RusGo

- PC TWA: Permissible Concentration-Time Weighted Average
- PC STEL: Permissible Concentration-Short Term Exposure Limit
- IARC: International Agency for Research on Cancer
- ACGIH: American Conference of Governmental Industrial Hygienists
- STEL: Short Term Exposure Limit
- TEEL: Temporary Emergency Exposure Limit,
 IDLH: Immediately Dangerous to Life or Health Concentrations
- ES: Exposure Standard
- OSF: Odour Safety Factor
- NOAEL: No Observed Adverse Effect Level
- LOAEL: Lowest Observed Adverse Effect Level TLV: Threshold Limit Value
- LOD: Limit Of Detection
- OTV: Odour Threshold Value
- BCF: BioConcentration Factors
- BEI: Biological Exposure Index
- DNEL: Derived No-Effect Level
- PNEC: Predicted no-effect concentration
- AIIC: Australian Inventory of Industrial Chemicals
- DSL: Domestic Substances List
- NDSL: Non-Domestic Substances List
- IECSC: Inventory of Existing Chemical Substance in China
 EINECS: European INventory of Existing Commercial chemical Substances
- ELINCS: European List of Notified Chemical Substances
- NLP: No-Longer Polymers
- ENCS: Existing and New Chemical Substances Inventory
- KECI: Korea Existing Chemicals Inventory
 NZIOC: New Zealand Inventory of Chemicals
- PICCS: Philippine Inventory of Chemicals and Chemical Substances
- TSCA: Toxic Substances Control Act
- TCSI: Taiwan Chemical Substance Inventory
- INSQ: Inventario Nacional de Sustancias Químicas
- NCI: National Chemical Inventory
 FBEPH: Russian Register of Potentially Hazardous Chemical and Biological Substances

This document is copyright.

Apart from any fair dealing for the purposes of private study, research, review or criticism, as permitted under the Copyright Act, no part may be reproduced by any process without written permission from CHEMWATCH.

TEL (+61 3) 9572 4700.