



OEM Satin Black

November 2022.



DESCRIPTION


RestoFinish OEM Satin Black is a two component Acrylic Polyurethane coating designed to maintain a superior appearance. It is derived from the factory finish of manufacturers commonly found on muscle cars.



SURFACE PREPARATION

Surface must be clean, dry and free of oil, grease, wax, rust, dirt or any foreign matter.

Existing Finishers and Primers: Ensure coatings are cured. Sand with minimum 500 grit dry or 800 wet. Use appropriate cleaning process with solvent or water based cleaners.




MIXING

Stir each component. Mix base, hardener and reducer as required by volume until fully blended.

Mix 4:1, equal to 4 parts OEM Satin Black to 1 part OEM Satin Black Hardener.

Can be reduced up to 20% with RestoFinish OEM Satin Black Reducer. Stir before use.

Allow 15 minutes induction time before application.



POT LIFE

Catalysed OEM Satin Black at 23°C is one hour.

Use within temperature range 15°C - 30°C.



APPLICATION

2 medium/wet coats. Full flash off until full even satin appearance all over.

15 - 30 mins between coats.

One coat is equal to 30-40 microns dry film build.



GUN SETUP AND CLEANING

Fluid tip 1.2 - 1.5mm @ 25-35 PSI.

Clean equipment with RestoFinish OEM Satin Black Reducer or quality gunwash.



DRYING TIME

Touch Dry (@25°C) 2 hr

Full cure (@25°C) 3 Days

HEALTH AND SAFETY FOR PROFESSIONAL USE ONLY. Full instructions must be read before use. Please refer to RestoFinish OEM Satin Black Safety Data Sheets (SDS) and product labels for full Health and Safety details and product handling instructions. **IMPORTANT:** This product contains hazardous materials and appropriate PPE (personal protective equipment) must always be used.

Products are suitable for professional use only. The data on this sheet indicate typical values. As application variables are a major factor in product performance, this information should serve as a general guide only. The data included in this application are based on our present knowledge and experience. RestoFinish assumes no responsibility or liability for use of this information. **UNLESS RESTOFINISH AGREES IN WRITING, RESTOFINISH ASSUMES NO WARRANTIES, EXPRESS OR IMPLIED, AND REPUDIATES ALL IMPLIED WARRANTIES INCLUDING WARRANTIES OF MERCHANTABILITY OR SUITABILITY FOR A PARTICULAR USE OR FREEDOM FROM PATENT INFRINGEMENT. RESTOFINISH WILL NOT BE LIABLE FOR ANY INCIDENTAL, SPECIAL OR SIGNIFICANT DAMAGES.** Your only remedy for any fault in this product is the replacement of the defective product, or a refund of the product purchase price, at our discretion. The latest version supersedes all preceding versions. You can obtain the most recent version from our website www.restofinish.com.au or directly from your sales agent. It is the responsibility of the beneficiary of our products to verify that any proprietary rights and existing laws and legislation are observed. RestoFinish© (a division of Global Finish Pty Ltd). All rights reserved. v0922

IN AN EMERGENCY DIAL 000 (AUS) or 111 (NZ) POLICE OR FIRE BRIGADE

RESTOFINISH A Division of Global Finish Pty Ltd 6/8 Stockyard Place, West Gosford NSW Australia 2250

Telephone: + 61 (2) 4321 0339 Facsimile: + 61 (2) 4321 0338 Email: info@restofinish.com.au www.restofinish.com.au