



AS1 ANTI SLIP ADDITIVE 1

JANUARY 2020

Product Data

AS 1 is high purity silica sand (50-70 mesh), used with coatings such as Amerlock 2 to provide an anti-slip finish.

Uses

May be broadcast onto wet / tacky paint surface, or premixed with paint.

When applied by broadcast method, overcoat with another coat of paint at the appropriate time.

When premixing into paint, add 300g per litre of catalysed Amerlock 2.

Apply with a mastic spray gun, such as Binks 7E2 with 64 x 191 nozzle, or Binks 18D with 69C x 191 nozzle.

A short nap roller may also be used.

Must keep paint well agitated, once AS 1 has been added.

Packaging

3kg in a 2L can

Health and Safety

Avoid breathing dust, as this may cause silicosis.

Dust may irritate eyes.

Wear dust mask and safety glasses.

First Aid

If swallowed, give small quantities of water.

If in eye, flush out with a gentle stream of clean water, for 15 minutes.

If inhaled, remove the patient from the affected area to an area of clean air.

For further details, read MSDS or contact National Poisons Centre: Tel 0800 POISON, 0800 764 766.

Technical information given verbally or in writing is based on knowledge and research, given in good faith and believed to be reliable, but no guarantee of accuracy is made or implied. Since methods and conditions of use are beyond our control, all merchandise is sold and received subject to the condition that our liability whether express or implied for any defect in quality, or for any lack of fitness for the specified use thereof, is limited to the return of the purchase price if written claim is made within 14 days from date of delivery. It is recommended that the user makes his or her own tests to determine the suitability of the product for his own requirements. Freedom from patent restrictions is not implied.

PPG Industries NZ Ltd • 5 Monahan Road • Mt Wellington • Auckland • Phone 0800-263 766 • Fax 0800-659 377