



Product Guide

2024


Description

210-0503/XX Polyurethane two-component topcoat with very good surface hardness, excellent water resistance, good resistance to marking and excellent hiding power. Excellent drying qualities allow the applicator to deliver a silky smooth in an economical time frame. This product in mixed colours has excellent coverage.

Link Products:		Curing Time: Coat: 1-2
812-88	Polyurethane Non-Yellowing Hardener	Drying Times: 20c
922-03/05	Polyurethane Thinner	Touch Times: 30-40 Minutes
Mixing Ratio:		Pot life :3 Hours
2:1	Thin 20-30%	Colour: Clear/Colour Match

Points to note:

During the summer, or in tropical areas, its preferable to use slow drying thinner. Tintable with 241 range up to 20%



2:1 with 812-88
+10-30% 922-03/05



Set up/air Pressure
1.4mm 2 Bar



Set up/air Pressure
06 or 09 Tip 90-120psi



Apply 1 to 2 coats



Flash for 10mins
@20°C after each coat



30-40min
Touch Dry @20°C

During the summer, or in hot or humid temperatures, it is preferable to use a slow thinner.

SQM 7.9 M2/L RFU