

## TECHNICAL DATA SHEET

# MAXISTRIP 30

MaxiStrip 30 is an all-purpose paint stripper used to target removal of failing topcoats, as a prep tool to reaching suitable substrate or for complete removal of all layers to bare substrate.

## FOR USE ON THE FOLLOWING SURFACES



### TIMBER

- Weatherboards
- Window frames
- Decks
- Doors



### METAL

- Roller doors
- Roofs
- Vehicles
- Powder coated window frames



### BRICK & BLOCK

- Painted brick
- Swimming pools
- Cow sheds
- Road paint



## BENEFITS OF MAXISTRIP 30

### MULTI PURPOSE

MaxiStrip 30 works on 2-pot, acrylic, enamel, varnish, powder coating and lacquer. An ideal prep tool for removal of failing topcoats, through to complete removal back to bare substrate. Also used for graffiti removal.

### RAPID ACTION

MaxiStrip 30 is made to denature coatings within 30 minutes in warm weather. Working deep to blister and soften even the most stubborn paints. It is fast, efficient and cost-effective.

### EXCELLENT ADHESION

Spray or brush on MaxiStrip 30 as thick as the layers need to be removed.

### REDUCED SITE CONTAMINATION

MaxiStrip 30 has a gel like texture due to its unique inbuilt surfactant, this fully encapsulates coatings wet as they are removed. The remaining surface should then be scrubbed with water and a scouring pad to achieve a clean and suitable surface for recoating.

## APPLICATION METHODS



Use a natural fibre brush to apply an even coat as thick as the number of coatings you want to take off.



MaxiStrip is made to be sprayed through out specially designed Indus20, available for hire or purchase from our distributors.

## REMOVAL METHODS



Scrape off with a tungsten carbide scraper or firm plastic spatula.



A stiff bristled nylon brush works at removing denatured coatings from deep crevasses.



If no lead is present, a water blaster with INDUSTRIAL FELT to trap particulate residue also works. Water blasting can be effective, but it is messy and requires care and skill to keep residue contained. Dispose of solid paint waste in accordance with local regulations.

## APPLICATION RECOMMENDATIONS

Apply a small test application to determine dwell time, application thickness, final removal and cleanup methods.

**APPLICATION TEMPERATURE:** Between 5 degrees - 40 degrees Celsius

**OPTIMUM COVERAGE:** 4m<sup>2</sup> per litre

**DWELL TIME:** Between 15 - 45 minutes (If it's wet it's still working. Do not allow to dry)

## CONTACT US

**CALL** 07 846 1339

**EMAIL** [info@systemax.co.nz](mailto:info@systemax.co.nz)

**VISIT** [www.systemax.co.nz](http://www.systemax.co.nz)

**ADDRESS**

23 Ellis Street, Frankton, Hamilton

**SYSTEMAX**

## PRECAUTIONS FOR USE & STORAGE

Follow all local safety, disposal, and transportation regulations. Check the Safety Data Sheet (SDS) and individual product label carefully before use.

## TECHNICAL CHARACTERISTICS

Physical description of colour:

**Viscous light bluish opalescent fluid**

Boiling point:

**39 degrees celsius**

Specific gravity:

**1.10**

Storage temperature:

**0-30 degrees celsius**

Non-Flammable