



295 LUSTALUX

JANUARY 2020

Quick Air Dry Alkyd

Product Data

Lustalux is a fast air dry spraying enamel, based on styrenated alkyd, with the following features:

- Exceptionally fast drying
- Excellent spraying characteristics
- High gloss
- One coat finish for economical work
- Fair abrasion resistance
- Fair solvent resistance
- Fair durability

Uses

As a high gloss finish for agricultural equipment, machinery etc, where an economical, easily applied system is required, and quick drying is desirable.

Colour Availability

Black, white, tinted solid and metallic colours available at Point Of Sale.

Packaging

1L, 4L, 20L

Substrates

Steel and ferrous metals.

Aluminium / galvanised steel / zintec – MUST be etch primed before applying rest of system.

Total Solids Content

49.0% (wt), 33.5% (vol) – for white.

Thinning and Clean Up

Cold conditions – Thin 10-25% with 254 Enamel Reducer MF.

Normal conditions – Thin 10-25% with 475 Enamel Reducer MI.

Hot conditions – Thin 5-10% with a blend of 475 Enamel Reducer MI and 539R Acrylic Retarder.

Airless spray – Thin 10-20% with 475 Enamel Reducer MI

Clean gun and equipment with 254 or 475 Reducers.

Application

Spray – conventional or airless.

Drying

Dust free: 5-10 minutes

Touch dry: 15-30 minutes

Hard dry: 6-12 hours, with full cure in 36-48 hours

Recoat: On 1833 or bare steel – recoat wet on wet if required. On 1030, 238 or 1850 Primers – recoat any time. Sand between coats if allowed to dry overnight.

Theoretical Coverage

Approximately 8.5 sq. m/litre @ 40µm DFT – for white.

Surface Preparation

Steel – Remove rust by blasting to SA2.5, or by using power tools or sanding. Degrease, prime.

Aluminium – Degrease, then scour with Scotchbrite. Degrease, prime.

Galv – Clean and degrease. Use a proprietary acid wash if surface has been chromate treated. Prime.

Health and Safety

Avoid breathing vapour. Use with adequate ventilation. High concentrations of vapour may cause headache or nausea, affect the nervous system and respiration.

Do not use in the presence of naked flame or other sources of ignition. Store away from heat.

Wear safety glasses / goggles, an air supplied respirator or hood and PVC or nitrile chemical handling gloves. Persons with a history of respiratory problems are advised not to use this product or any other two pack polyurethane.

Store / dispose of residues in accordance with local body regulations.

First Aid

If poisoning occurs, contact a doctor. The Poisons Information Centre may be of assistance – telephone 0800 POISON (0800 764 766).

If swallowed, do NOT induce vomiting. Give a glass of water to drink and get medical attention urgently.

If affected by vapour, get into fresh air immediately.

If splashed into the eyes, flush them with copious quantities of clean water for 15 minutes and get urgent medical attention.

If splashed onto skin, wash with soap and water.

For further information, refer to the Material Safety Data Sheet for this product.

CAUTION:

Improper use and handling of this product can be hazardous to health.

Do not use this product without first taking all appropriate safety measures to prevent property damage and injuries. These measures may include, without limitation: implementation of proper ventilation, use of proper lamps, wearing of proper protective clothing and masks, tenting and proper separation of application areas. Consult your supervisor. Proper ventilation and protective measures must be provided during application and drying to keep spray mists and vapour concentrations within safe limits and to protect against toxic hazards. Necessary safety equipment must be used and ventilation requirements carefully observed, especially in confined or enclosed spaces, such as tank interiors and buildings.

This product is to be used by those knowledgeable about proper application methods. PPG Industries makes no recommendation about the types of safety measure that may need to be adopted because these depend on application environment and space, of which PPG Industries is unaware and over which it has no control.

If you do not fully understand these warnings and instructions or if you cannot strictly comply with them, do not use the product.



295 LUSTALUX

Substrate Systems

Preparation

Steel – Remove rust, clean and degrease, or blast to Class 2 ½ if indicated

Aluminium – Scour with Scotchbrite and degrease

Galv – Clean and degrease

Substrate / Recommended System	WFT / DFT (Microns)	Overcoat Time @ 20 Degrees C	Overcoat Preparation
STEEL (Interior use only) 1 st coat 1833 UltraEtch Primer OR 1030 Protecto Primer 2 nd coat 295 Lustalux	110-140 / 20-25 55-85 / 25-40 105-145 / 35-50	1-6 hrs Overnight 1-8 hrs Overnight	N/A Sand 320 N/A Sand 360
STEEL (Interior / Exterior use) 1 st coat 238 Primacote OR 1850 Zinchro Primer 2 nd coat 295 Lustalux	70-110 / 25-40 65-125 / 25-50 105-145 / 35-50	1-8 hrs Overnight 1-8 hrs Overnight	N/A Sand 360 N/A Sand 360
ALUMINIUM / GALVANISED STEEL (2 coat system) 1 st coat 1833 UltraEtch Primer 2 nd coat 295 Lustalux	60-90 / 8-12 105-145 / 35-50	1 hour	N/A
ALUMINIUM / GALVANISED STEEL (3 coat system) 1 st coat 719 Polyetch 2 nd coat 238 Primacote OR 1850 Zinchro Primer 3 rd coat 295 Lustalux	70-100 / 7-10 70-110 / 25-40 65-125 / 25-50 105-145 / 35-50	15-20' 1-8 hrs Overnight 1-8 hrs Overnight	N/A N/A Sand 360 N/A Sand 360

WFT = Wet Film Thickness

DFT = Dry Film Thickness

Technical information given verbally or in writing is based on knowledge and research, given in good faith and believed to be reliable, but no guarantee of accuracy is made or implied. Since methods and conditions of use are beyond our control, all merchandise is sold and received subject to the condition that our liability whether express or implied for any defect in quality, or for any lack of fitness for the specified use thereof, is limited to the return of the purchase price if written claim is made within 14 days from date of delivery. It is recommended that the user makes his or her own tests to determine the suitability of the product for his own requirements. Freedom from patent restrictions is not implied.