



779 CAPRINAMEL

FEBRUARY 2021

2K Polyurethane Spraying Enamel

Product Data

CAPRINAMEL is a two component polyurethane spraying enamel with the following features:

- High hardness in a range of colours and gloss levels
- Very good exterior durability.
- Resistant to a wide range of chemicals and cleaning agents.
- Excellent abrasion resistance.
- Good solvent resistance.

The hardener is based on aliphatic polyisocyanate.

Uses

For use on structural steel, agricultural equipment, trucks, buses – surfaces where a durable, chemical resistant, easily cleaned surface is required.

Note – CAPRINAMEL Clear is not for exterior use.

Colour Availability

Black, White and Tinted colours available at Point Of Sale.

Gloss levels available: G10, G30, G50, G100 Full Gloss

Packaging

0779A Base – 4L, 20L

0779B Hardener – 1L

Substrates

Steel and ferrous alloys, suitably primed.

Aluminium / galvanised steel – MUST be preprimed with 719 Polyetch or 1833 UltraEtch.

Sanded original baked enamel or 2K enamel in good condition.

Thinning and Clean Up

When catalysed with 0779B, thin as follows:

- Normal and Cold conditions – 20-30% with 254
- Warm conditions – 20-30% with mixture of 475

Application

Spray – Conventional, pressure pot, airless.

Do NOT apply by hot spray.

Brush – Small areas only.

Drying

Dust free – 25'

Print free – 1 hour

Dry to tape – 24 hours

Hard dry – 24 hours

Cut and polish – 36 hours to 7 days (depends on ambient conditions).

Recoat time – Wet on wet, under 2 hours OR over 24 hours with sanding.

Theoretical Coverage

Approximately 8.7 sq. m/litre @ 40µm DFT (catalysed)

Practical coverage rates will be lower than theoretical and this must be taken into consideration when calculating costs.

Mixing Ratio

Mix 4L 0779A CAPRINAMEL Base with 1L 0779B

Pot Life

4 hours at 21degC

Surface Preparation

Steel – Remove rust by blasting to SA2.5, or by using power tools or sanding. Degrease.

Aluminium – Degrease, then scour with Scotchbrite. Degrease again.

Galvanised steel – Clean and degrease. Use a proprietary acid wash if surface has been chromate treated.

Original finish – Sand and dust down. Degrease.

Safety Precautions

Read each component's material safety data sheet before use. Mixed material has hazards of each component. Safety precautions must be strictly followed during storage, handling and use.

Health and Safety

Avoid breathing vapour. Use with adequate ventilation. High concentrations of vapour may cause headache or nausea, affect the nervous system and respiration. When catalysed this product contains isocyanates, which are harmful by inhalation. Refer to Code of Practice for the Safe Handling of Isocyanates 1989 (or updates) for details on handling isocyanate material.

Do not use in the presence of naked flame or other sources of ignition. Store away from heat.

Wear safety glasses / goggles, an air supplied respirator or hood and PVC or nitrile chemical handling gloves. Persons with a history of respiratory problems are advised not to use this product or any other two pack polyurethane.

Store / dispose of residues in accordance with local body regulations.

First Aid

If poisoning occurs, contact a doctor. The Poisons Information Centre may be of assistance – telephone 0800 POISON (0800 764 766).

If swallowed, do NOT induce vomiting. Give a glass of water to drink and get medical attention urgently.

If affected by vapour, get into fresh air immediately.

If splashed into the eyes, flush them with copious quantities of clean water for 15 minutes and get urgent medical attention.

If splashed onto skin, wash with soap and water.

For further information, refer to the Material Safety Data Sheet for this product.

CAUTION:

Improper use and handling of this product can be hazardous to health.

Do not use this product without first taking all appropriate safety measures to prevent property damage and injuries. These measures may include, without limitation: implementation of proper ventilation, use of proper lamps, wearing of proper protective clothing and masks, tenting and proper separation of application areas. Consult your supervisor. Proper ventilation and protective measures must be provided during application and drying to keep spray mists and vapour concentrations within safe limits and to protect against toxic hazards. Necessary safety equipment must be used and ventilation requirements carefully observed, especially in confined or enclosed spaces, such as tank interiors and buildings.

This product is to be used by those knowledgeable about proper application methods. PPG Industries makes no recommendation about the types of safety measure that may need to be adopted because these depend on application environment and space, of which PPG Industries is unaware and over which it has no control.

If you do not fully understand these warnings and instructions or if you cannot strictly comply with them, do not use the product.



779 CAPRINAMEL

Substrate Systems

Preparation

Steel – Remove rust, clean and degrease, or blast to Class 2 ½ if indicated

Aluminium – Scour with Scotchbrite and degrease

Galv – Clean and degrease

Substrate / Recommended System	DFT (Microns)	Overcoat Time @ 20 Degrees C	Overcoat Preparation
STEEL			
1 st coat 178HS Primer	50-75	16 hrs	Sand 360
2 nd coat 779 CAPRINAMEL	37-50	16 hrs plus	Sand 320
STEEL (Aggressive conditions)			
1 st coat 719 Polyetch	7-10	1-8 hrs	N/A
2 nd coat AMERCOAT 488	50-75	16 hrs plus	Sand 360
		3 hrs – 1 mth	N/A
OR 178 HS Primer	50-75	16 hrs	Sand 360
3 rd coat 779 CAPRINAMEL	37-50		
STEEL (Aggressive conditions)			
Blast to Class 2 ½			
1 st coat AMERCOAT 488	50-75	16 hrs plus	Sand 360
		3 hrs – 1 mth	N/A
2 nd coat 779 CAPRINAMEL	37-50		
ALUMINIUM / GALV (2 coat system)			
1 st coat 719 Polyetch	7-10	20' – 8 hrs	N/A
OR 1833 UltraEtch	8-12		
2 nd coat 779 CAPRINAMEL	37-50		
ALUMINIUM / GALV (3 coat system)			
1 st coat 719 Polyetch	7-10	1-8 hrs	N/A
2 nd coat AMERCOAT 488	50-76	16 hrs plus	Sand 360
		3 hrs – 1 mth	N/A
OR 178HS Primer	50-75	16 hrs	Sand 360
3 rd coat 779 CAPRINAMEL	37-50		

DFT = Dry Film Thickness

Technical information given verbally or in writing is based on knowledge and research, given in good faith and believed to be reliable, but no guarantee of accuracy is made or implied. Since methods and conditions of use are beyond our control, all merchandise is sold and received subject to the condition that our liability whether express or implied for any defect in quality, or for any lack of fitness for the specified use thereof, is limited to the return of the purchase price if written claim is made within 14 days from date of delivery. It is recommended that the user makes his or her own tests to determine the suitability of the product for his own requirements. Freedom from patent restrictions is not implied.